


OIL ANALYSIS REPORT



NORMAL



Machine Id Component **Diesel Engine**

PETRO CANADA DURON UHP 5W30 (--- G

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

L)			Feb 2024			
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0117693		
Sample Date		Client Info		23 Feb 2024		
Machine Age	mls	Client Info		0		
Oil Age	mls	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINAT	ION	method	limit/base	current	history1	history2
-uel		WC Method	>5	<1.0		
Nater		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METAL	S	method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>100	0		
Chromium	ppm	ASTM D5185m	>20	<1		
Nickel	ppm	ASTM D5185m	>4	0		
Γitanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m	>3	0		
Aluminum	ppm	ASTM D5185m	>20	1		
_ead	ppm	ASTM D5185m	>40	<1		
Copper	ppm	ASTM D5185m	>330	<1		
Γin	ppm	ASTM D5185m	>15	<1		
/anadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	188		
Barium	ppm	ASTM D5185m	0	0		
Molybdenum	ppm	ASTM D5185m	64	62		
Manganese	ppm	ASTM D5185m	0	<1		
Magnesium	ppm	ASTM D5185m	1160	514		
Calcium	ppm	ASTM D5185m	820	1097		
Phosphorus	ppm	ASTM D5185m	1160	664		
Zinc	ppm	ASTM D5185m	1260	771		
Sulfur	ppm	ASTM D5185m	3000	2804		
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	11		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	2		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0		
Nitration	Abs/cm	*ASTM D7624	>20	4.2		
Sulfation	Abs/.1mm	*ASTM D7415	>30	15.0		
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	10.2		



OIL ANALYSIS REPORT





Visc @ 100°C	cSt	ASTM D445	11.9	10.9		
GRAPHS						
Iron (ppm)				Lead (ppm)		
Severe				Severe		
E 150				E Abnormal		
150 Abnormal	***************************************			Abnormal		
50				20		
Feb23/24			Feb23/24	Feb23/24		Feb23/24 -
			윤			Feb,
Aluminum (ppm)				Chromium ((ppm)	
40 Severe				40 + Severe		
Abnormal				Abnormal		
10 +	***************************************			10+		-
0			_	0		
Feb 23/24			Feb23/24	Feb23/24		Feb23/24
ت Copper (ppm)			æ	్ల Silicon (ppm	1)	3
400 Severe Publication				80 Severe	.,	
300				60+		
틀 200				Abnormal		
100				20+		
0 45			24	0 +4		
Feb23/24			Feb23/24	Feb23/24		Feb23/24
Viscosity @ 100°0				Base Numb	er	
16 7				(a) 12.0 Base	***************************************	
Abnormal Base				Base Number (mg KOH/t0)		
St (1	***************************************		nnnni	a 6.0 + 1		
Abnormal				% 2.0+		
∞ Feb23/24 —			Feb23/24 +	Feb23/24		Feb23/24 -
Feb2			Feb2	Feb2		Feb 2





Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Lab Number : 06105019 Unique Number: 10903249

: PCA0117693

Received **Tested**

Diagnosed Test Package : MOB 1 (Additional Tests: TBN)

: 01 Mar 2024 : 04 Mar 2024 - Sean Felton

: 29 Feb 2024

2345 S DESPLAINES NORTH RIVERSIDE, IL

US 60546 Contact: Service Manager vznrdpw@gmail.com

VILLAGE OF NORTH RIVERSIDE

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: VILNOR [WUSCAR] 06105019 (Generated: 03/04/2024 18:07:03) Rev: 1

Contact/Location: Service Manager - VILNOR

T:

F: