




PROBLEM SUMMARY

Sample Rating Trend



FUEL




Machine Id
923012-565

Component
Diesel Engine


Fluid
PETRO CANADA DURON SHP 15W40 (28 QTS)

COMPONENT CONDITION SUMMARY

▲ Fuel Dilution



▲ Viscosity @ 100°C



RECOMMENDATION

We advise that you check the fuel injection system. The oil change at the time of sampling has been noted. We recommend an early resample to monitor this condition.

PROBLEMATIC TEST RESULTS

Sample Status				SEVERE	MARGINAL	SEVERE
Fuel	%	ASTM D3524	>3.0	▲ 7.9	▲ 3.1	▲ 7.2
Visc @ 100°C	cSt	ASTM D445	15.4	▲ 11.5	12.6	▲ 12.3

Customer Id: GFL622
Sample No.: GFL0110280
Lab Number: 06105077
Test Package: FLEET



To manage this report scan the QR code

To discuss the diagnosis or test data:
Wes Davis +1 905-569-8600 x223
wesd@wearcheck.ca

To change component or sample information:
Customer Service +1 1-800-237-1369
customerservice@wearcheck.com

RECOMMENDED ACTIONS

Action	Status	Date	Done By	Description
Resample	---	---	?	We recommend an early resample to monitor this condition.
Check Fuel/injector System	---	---	?	We advise that you check the fuel injection system.

HISTORICAL DIAGNOSIS

01 Dec 2023 Diag: Jonathan Hester

FUEL



No corrective action is recommended at this time. Resample at the next service interval to monitor. All component wear rates are normal. Light fuel dilution occurring. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

view report



19 Oct 2023 Diag: Don Baldrige

FUEL



We advise that you check the fuel injection system. Oil and filter change at the time of sampling has been noted. We recommend an early resample to monitor this condition. All component wear rates are normal. There is a high amount of fuel present in the oil. Fuel is present in the oil and is lowering the viscosity. The BN result indicates that there is suitable alkalinity remaining in the oil.

view report



01 Sep 2023 Diag: Sean Felton

NORMAL



Resample at the next service interval to monitor. All component wear rates are normal. There is no indication of any contamination in the oil. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


view report





OIL ANALYSIS REPORT

Sample Rating Trend



FUEL



Machine Id
923012-565

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (28 QTS)

DIAGNOSIS

▲ Recommendation

We advise that you check the fuel injection system. The oil change at the time of sampling has been noted. We recommend an early resample to monitor this condition.

Wear

All component wear rates are normal.

▲ Contamination

There is a high amount of fuel present in the oil. Tests confirm the presence of fuel in the oil.

▲ Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. Fuel is present in the oil and is lowering the viscosity. The oil is no longer serviceable due to the presence of contaminants.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	GFL0110280	GFL0102811	GFL0090465
Sample Date	Client Info	27 Feb 2024	01 Dec 2023	19 Oct 2023
Machine Age	hrs	23205	22829	22625
Oil Age	hrs	580	22625	580
Oil Changed	Client Info	Changed	Not Changd	Changed
Sample Status		SEVERE	MARGINAL	SEVERE

CONTAMINATION

method	limit/base	current	history1	history2
Water	WC Method >0.2	NEG	NEG	NEG
Glycol	WC Method	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >90	58	23	68
Chromium	ppm ASTM D5185m >20	3	1	2
Nickel	ppm ASTM D5185m >2	0	<1	0
Titanium	ppm ASTM D5185m >2	0	0	0
Silver	ppm ASTM D5185m >2	0	<1	0
Aluminum	ppm ASTM D5185m >20	3	2	2
Lead	ppm ASTM D5185m >40	1	<1	2
Copper	ppm ASTM D5185m >330	2	1	10
Tin	ppm ASTM D5185m >15	<1	<1	<1
Vanadium	ppm ASTM D5185m	0	0	0
Cadmium	ppm ASTM D5185m	0	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 0	7	6	2
Barium	ppm ASTM D5185m 0	0	0	0
Molybdenum	ppm ASTM D5185m 60	55	60	61
Manganese	ppm ASTM D5185m 0	<1	<1	<1
Magnesium	ppm ASTM D5185m 1010	800	890	914
Calcium	ppm ASTM D5185m 1070	947	1037	1046
Phosphorus	ppm ASTM D5185m 1150	936	1014	940
Zinc	ppm ASTM D5185m 1270	1107	1227	1185
Sulfur	ppm ASTM D5185m 2060	2515	2978	2487

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >25	7	5	8
Sodium	ppm ASTM D5185m	11	7	26
Potassium	ppm ASTM D5185m >20	1	<1	1
Fuel	% ASTM D3524 >3.0	▲ 7.9	▲ 3.1	▲ 7.2

INFRA-RED

method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >6	1.3	0.6	1.4
Nitration	Abs/cm *ASTM D7624 >20	10.5	7.2	10.3
Sulfation	Abs/.1mm *ASTM D7415 >30	21.3	18.8	21.9


FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	17.7	13.7	17.8
Base Number (BN)	mg KOH/g ASTM D2896 9.8	7.4	8.4	6.6




OIL ANALYSIS REPORT


▲ Fuel Dilution



▲ Viscosity @ 100°C







Base Number



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	▲ 11.5	12.6	▲ 12.3

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0110280
Lab Number : 06105077
Unique Number : 10903307
Test Package : FLEET (Additional Tests: FuelDilution, PercentFuel)

Received : 29 Feb 2024
Tested : 04 Mar 2024
Diagnosed : 04 Mar 2024 - Wes Davis

GFL Environmental - 622 - Traverse City Hauling
 160 Hughes Dr
 Traverse City, MI
 US 49686
Contact: GARY BREWER

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: