

OIL ANALYSIS REPORT

Sample Rating Trend

VISUAL METAL



DT608 Component **Rear Differential**

CHEVRON RPM SYNTHETIC GEAR 75W90 (3 mls)



Recommendation

The oil change at the time of sampling has been noted. We advise that you inspect for the source(s) of metal. Resample at the next service interval to monitor.

Wear


High concentration of visible metal present. All component wear rates are normal.

Contamination

There is no indication of any contamination in the

Fluid Condition


The condition of the oil is acceptable for the time in service.



SAMPLE INFOR	IVIATION	memou	IIIIIIIIIIIIIII	Current	HISTORY	HISTOLYZ
Sample Number		Client Info		PCA0089116	PCA0080446	PCA0045189
Sample Date		Client Info		25 Jan 2024	28 Nov 2022	14 Apr 2021
Machine Age	mls	Client Info		229446	191474	0
Oil Age	mls	Client Info		67481	0	0
Oil Changed		Client Info		Changed	N/A	Not Changd
Sample Status				ABNORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Water		WC Method	>.2	NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>1200	265	161	133
Chromium	ppm	ASTM D5185m	>8	<1	<1	1
Nickel	ppm	ASTM D5185m	>20	0	0	1
Titanium	ppm	ASTM D5185m	>4	<1	<1	<1
Silver	ppm	ASTM D5185m		0	<1	0
Aluminum	ppm	ASTM D5185m	>30	25	4	7
Lead	ppm	ASTM D5185m	>25	0	0	0
Copper	ppm	ASTM D5185m	>50	<1	1	<1
Tin	ppm	ASTM D5185m	>5	0	<1	0
Antimony	ppm	ASTM D5185m	>5			0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		197	238	196
Barium	ppm	ASTM D5185m		<1	0	0
Molybdenum	ppm	ASTM D5185m		11	12	0
Manganese	ppm	ASTM D5185m		4	3	6
Magnesium	ppm	ASTM D5185m		71	70	3
Calcium	ppm	ASTM D5185m		187	176	13
Phosphorus	ppm	ASTM D5185m		1384	1261	1383
Zinc	ppm	ASTM D5185m		138	137	11
Sulfur	ppm	ASTM D5185m		22917	25056	21371
Lithium	ppm	ASTM D5185m				
	ITC	method	limit/base	current	history1	history2
CONTAMINAN	110	method				
CONTAMINAN Silicon	ppm		>230	40	12	14
			>230	40 1	12 1	14 3



OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	▲ HEAVY	MODER	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	110	85.8	88.5	101


SAMPLE IMAGES	method	limit/base	current	history1	history2
Color			no image	no image	no image
Bottom			no image	no image	no image

GRAPHS

Ferrous Alloys











Laboratory Sample No. Lab Number : 06105522

Test Package : FLEET

: PCA0089116

Unique Number : 10903752

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 29 Feb 2024 **Tested** : 01 Mar 2024

: 04 Mar 2024 - Don Baldridge

NW WHITE & CO - GREER DIVISION

1060 ROGERS BRIDGE RD DUNCAN, SC US 29334

Contact: Matt Quinlan mquinlan@nwwhite.com

T: (864)905-8506

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Diagnosed

F: