

OIL ANALYSIS REPORT

Sample Rating Trend





Machine Id DT746 Component

Transmission (Auto) Fluid COGNIS EMGARD 2805 ATF (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the fluid.


Fluid Condition

The condition of the fluid is acceptable for the time in service.

			52021	Dec2022 Jan20	29	
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0089132	PCA0080426	PCA0036586
Sample Date		Client Info		25 Jan 2024	14 Dec 2022	12 Feb 2021
Machine Age	mls	Client Info		145041	103966	28425
Oil Age	mls	Client Info		41075	103966	0
Oil Changed		Client Info		Not Changd	Changed	Not Changd
Sample Status				NORMAL	NORMAL	ABNORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Water		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>220	83	146	57
Chromium	ppm	ASTM D5185m		0	<1	0
Nickel	ppm	ASTM D5185m	>5	0	<1	0
Titanium	ppm	ASTM D5185m	20	0	0	0
Silver	ppm	ASTM D5185m	>5	0	0	0
Aluminum	ppm	ASTM D5185m		24	41	16
Lead		ASTM D5185m	>95		45	28
Copper	ppm ppm	ASTM D5185m	>95 >60	15 14	45 22	20
		ASTM D5185m		2	4	2
Tin	ppm		>10			
Antimony	ppm	ASTM D5185m	>2			0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		72	87	112
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	1	<1
Manganese	ppm	ASTM D5185m		<1	2	<1
Magnesium	ppm	ASTM D5185m		<1	<1	0
Calcium	ppm	ASTM D5185m		97	47	36
Phosphorus	ppm	ASTM D5185m		240	289	274
Zinc	ppm	ASTM D5185m		0	0	0
Sulfur	ppm	ASTM D5185m		1450	713	666
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	7	7	3
Sodium	ppm	ASTM D5185m		4	7	5
Potassium	ppm	ASTM D5185m	>20	1	4	2
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	NONE	A MODER
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG		By: Matt Quinlar



OIL ANALYSIS REPORT



Ferrous Alloys	ES met	hod lin	nit/base cu no in no in	nrent h	iistory1 ł	5.0 history2 o image o image
Color Bottom GRAPHS Ferrous Alloys	Dec1422		no in no in	nage no	image no	o image
Bottom GRAPHS Ferrous Alloys Chromium nickel Non-ferrous Metals		b2/52upf	no in			
GRAPHS Ferrous Alloys		Paragener Para		nage no	image no	o image
Ferrous Alloys		PT/S2/upf				
Ferrous Alloys		Parisized A				
iron chromium nickel		+C/SZ/uer				
	~~	\sum				
Feb 12/21	4/22	5/24				
	Dec14/22	Jan25/24				
Viscosity @ 40°C	1					
Base						
Abnormal						
\sim						
	5		_			
Feb12/2)ec14/2	an 25/2				
		, Cary, NC : 29 Feb : 02 Mar	27513 2024 2024	106	0 ROGERS BR DUN	RIDGE F NCAN, S JS 293
	Viscosity @ 40°C Abnormal Base Abnormal Ab	Viscosity @ 40°C Abnormal Base Abnormal Base Abnormal Comparison Base Comparison	Viscosity @ 40°C Abnormal Base Base Abnormal Control of the second	Viscosity @ 40°C	Viscosity @ 40°C	Viscosity @ 40°C

