

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Machine Id **707388** Component

Diesel Engine

PETRO CANADA DURON SHP 10W30 (--- 0

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

rts)				Feb2024		
SAMPLE INFOR	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0093353		
Sample Date		Client Info		27 Feb 2024		
Machine Age	mls	Client Info		380532		
Oil Age	mls	Client Info		0		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINA	TION	method	limit/base	current	history1	history2
- uel		WC Method	>5	<1.0		
Vater		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METAI	LS	method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>100	30		
Chromium	ppm	ASTM D5185m	>20	1		
Nickel	ppm	ASTM D5185m	>4	<1		
Fitanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m	>3	0		
Aluminum	ppm	ASTM D5185m	>20	8		
ead	ppm	ASTM D5185m	>40	0		
Copper	ppm	ASTM D5185m	>330	8		
- Tin	ppm	ASTM D5185m	>15	<1		
/anadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	5		
Barium	ppm	ASTM D5185m	0	0		
Molybdenum	ppm	ASTM D5185m	50	64		
Manganese	ppm	ASTM D5185m	0	<1		
Magnesium	ppm	ASTM D5185m	950	941		
Calcium	ppm	ASTM D5185m	1050	1089		
Phosphorus	ppm	ASTM D5185m	995	1083		
Zinc	ppm	ASTM D5185m	1180	1308		
Sulfur	ppm	ASTM D5185m	2600	2922		
CONTAMINA	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	6		
Sodium	ppm	ASTM D5185m		2		
Potassium	ppm	ASTM D5185m	>20	6		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.5		
Nitration	Abs/cm	*ASTM D7624	>20	10.0		
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.7		
FLUID DEGRA	NOITAD	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	20.2		
Base Number (BN)		ASTM D2896		5.8		
(- 1 1)	99			-		



OIL ANALYSIS REPORT





Visc @ 100°C	cSt	ASTM D445	12.00	11.7		
GRAPHS						
Iron (ppm)				Lead (ppm	1)	
Severe				80 Severe		
Abnormal				Abnormal		
Abnormal			-	40 7 0	***************************************	
				0		
Feb 27/24			Feb27/24	Feb27/24		
			윤	_		
Aluminum (ppm)				Chromium 50 T	(ppm)	
Severe				40 - Severe		
Abnormal				20 - Abnormal		
		••••••		10 +	***************************************	
				0		
Feb27/24			Feb27/24	Feb27/24		
© Copper (ppm)			굔	≞ Silicon (pp	m)	
T Severe				Silicon (pp		
Abnormal				60-		
				Ē 40-		
				Abnormal 20		
			4	0		
Feb27/24			Feb27/24	Feb27/24		
Viscosity @ 100°	С		ш.	Base Num	ber	
				6.0		
Abnormal				B 4.0		
Base	***************************************			0.1.07 (mg kO)		
Abnormal				% 1.0+		
			24	0.0		
Feb27/24			Feb27/24	Feb27/24		





Laboratory

Sample No.

Lab Number : 06105730 Unique Number : 10903960

: PCA0093353

Received : 01 Mar 2024 **Tested** : 01 Mar 2024 Diagnosed

: 01 Mar 2024 - Wes Davis

US 19533 Contact: JAMEY RITZ jritz@millertransgroup.com T:

2666 LEISCZS BRIDGE RD

LEESPORT, PA

Test Package : MOB 1 (Additional Tests: TBN) To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: