




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
(YA139882) 020

Machine Id
2628

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (46 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	GFL0103792	GFL0076957	GFL0091183
Sample Date	Client Info	29 Feb 2024	31 Oct 2023	23 Aug 2023
Machine Age	hrs	21443	20809	0
Oil Age	hrs	634	7646	600
Oil Changed	Client Info	Changed	Changed	Not Changed
Sample Status		NORMAL	NORMAL	NORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >3.0	<1.0	<1.0	<1.0
Water	WC Method >0.2	NEG	NEG	NEG
Glycol	WC Method	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >165	16	14	15
Chromium	ppm ASTM D5185m >5	<1	<1	<1
Nickel	ppm ASTM D5185m >4	<1	<1	0
Titanium	ppm ASTM D5185m >2	0	0	0
Silver	ppm ASTM D5185m >2	0	<1	0
Aluminum	ppm ASTM D5185m >20	3	2	5
Lead	ppm ASTM D5185m >150	2	2	<1
Copper	ppm ASTM D5185m >90	<1	1	2
Tin	ppm ASTM D5185m >5	0	<1	<1
Vanadium	ppm ASTM D5185m	0	<1	0
Cadmium	ppm ASTM D5185m	0	<1	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 0	4	2	4
Barium	ppm ASTM D5185m 0	0	4	0
Molybdenum	ppm ASTM D5185m 60	64	59	66
Manganese	ppm ASTM D5185m 0	0	0	<1
Magnesium	ppm ASTM D5185m 1010	1107	862	1045
Calcium	ppm ASTM D5185m 1070	1247	1059	1231
Phosphorus	ppm ASTM D5185m 1150	1167	828	1153
Zinc	ppm ASTM D5185m 1270	1427	1191	1398
Sulfur	ppm ASTM D5185m 2060	3538	3019	3962

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >35	5	4	4
Sodium	ppm ASTM D5185m	3	3	4
Potassium	ppm ASTM D5185m >20	1	3	2

INFRA-RED



method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >7.5	0.3	0.7	0.3
Nitration	Abs/cm *ASTM D7624 >20	8.5	8.8	8.6
Sulfation	Abs/.1mm *ASTM D7415 >30	19.9	20.6	20.1

FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	16.3	16.6	16.3
Base Number (BN)	mg KOH/g ASTM D2896 9.8	8.0	8.2	8.3







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	13.6	13.6	13.6

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0103792
Lab Number : **06107022**
Unique Number : 10910519
Test Package : FLEET

GFL Environmental - 020 - Alamance
 703 East Gilbreath St
 Graham, NC
 US 27253
 Contact:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

richard.belcher@gflenv.com

T: (800)207-6618

F: (336)229-0526