


OIL ANALYSIS REPORT

San



NORMAL



700110

Component **Diesel Engine**

PETRO CANADA DURON SHP 10W30 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

GAL)						
		<u>L</u>		Feb 2024		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0099130		
Sample Date		Client Info		23 Feb 2024		
Machine Age	mls	Client Info		366244		
Oil Age	mls	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0		
Water		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	16		
Chromium	ppm	ASTM D5185m	>20	<1		
Nickel	ppm	ASTM D5185m	>4	<1		
Titanium	ppm	ASTM D5185m		2		
Silver	ppm	ASTM D5185m	>3	0		
Aluminum	ppm	ASTM D5185m	>20	3		
Lead	ppm	ASTM D5185m	>40	<1		
Copper	ppm	ASTM D5185m	>330	2		
Tin	ppm	ASTM D5185m	>15	<1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	5		
Barium	ppm	ASTM D5185m	0	0		
Molybdenum	ppm	ASTM D5185m	50	65		
Manganese	ppm	ASTM D5185m	0	<1		
Magnesium	ppm	ASTM D5185m	950	894		
Calcium	ppm	ASTM D5185m	1050	1103		
Phosphorus	ppm	ASTM D5185m	995	1060		
Zinc	ppm	ASTM D5185m	1180	1246		
Sulfur	ppm	ASTM D5185m	2600	3022		
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	7		
Sodium	ppm	ASTM D5185m		1		
Potassium	ppm	ASTM D5185m	>20	3		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.6		
Nitration	Abs/cm	*ASTM D7624	>20	10.1		
Sulfation	Abs/.1mm	*ASTM D7415	>30	23.1		
FLUID DEGRAD	NOITAC	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	20.3		
Base Number (BN)	mg KOH/g	ASTM D2896		5.3		
	9	222000				



OIL ANALYSIS REPORT





Visc @ 100°C	cSt	ASTM D445	12.00	12.0		
GRAPHS						
Iron (ppm)				Lead (ppm))	
250 Severe				Severe		
E 150				€ 60		
150 Abnormal			-	Abnormal	***************************************	
50				20		
Feb 23/24			Feb23/24	Feb23/24		Feb23/24 -
			Feb			Feb
Aluminum (ppm)				Chromium 50 _T	(ppm)	
40 Severe				40 Severe		
Abnormal				Abnormal		
10+				10		-
0				0		
Feb 23/24			Feb23/24	Feb23/24		Feb23/24
Copper (ppm)			Œ	Silicon (ppn	n)	Ĭ.
400 Severe Publication				80 - Severe		
300				60		
[200 -				Abnormal		
100				20		
0 + 4			124	0 1 4 2		
Feb23/24			Feb23/24	Feb23/24		Feb23/24
Viscosity @ 100°C				Base Numb	er	
16 Abnormal				86.0 5.0		
14 - Abnormal			-	X 4.0		
# T T T T T T T T T T T T T T T T T T T				(0) 5.0 - 1.		
Abnormal 8				% 1.0 0.0		
o Feb23/24 ₹			Feb23/24	Eb23/24		Feb23/24 -
Zeb.			Feb.	Feb,		Feb2
: WearCheck USA - 50	1 Madisor	n Ave., Cary	NC 27	513	MILLER TRUCK	LEASING #116





Laboratory

Sample No.

Lab Number : 06107196 Unique Number: 10910693

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : PCA0099130

Received **Tested**

Diagnosed Test Package : MOB 1 (Additional Tests: TBN)

: 04 Mar 2024 : 05 Mar 2024

: 05 Mar 2024 - Wes Davis

VINELAND, NJ US 08360 Contact: JOHN KEEN

1197 NORTH MAIN ROAD

jkeen@millertransgroup.com To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (856)696-5629

T: