




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
(YA144047) GFL035

Machine Id
3810

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (38 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	GFL0112959	GFL0071579	GFL0061690
Sample Date	Client Info	04 Mar 2024	11 Jul 2023	25 Jan 2023
Machine Age	hrs	0	18225	18225
Oil Age	hrs	14817	600	600
Oil Changed	Client Info	N/A	Changed	Changed
Sample Status		NORMAL	ATTENTION	NORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >3.0	<1.0	<1.0	<1.0
Water	WC Method >0.2	NEG	NEG	NEG
Glycol	WC Method	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >165	14	16	16
Chromium	ppm ASTM D5185m >5	<1	<1	<1
Nickel	ppm ASTM D5185m >4	0	0	0
Titanium	ppm ASTM D5185m >2	0	0	0
Silver	ppm ASTM D5185m >2	0	0	0
Aluminum	ppm ASTM D5185m >20	<1	19	1
Lead	ppm ASTM D5185m >150	<1	0	<1
Copper	ppm ASTM D5185m >90	1	<1	3
Tin	ppm ASTM D5185m >5	0	<1	<1
Vanadium	ppm ASTM D5185m	0	0	0
Cadmium	ppm ASTM D5185m	0	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 0	<1	2	11
Barium	ppm ASTM D5185m 0	0	<1	0
Molybdenum	ppm ASTM D5185m 60	59	69	64
Manganese	ppm ASTM D5185m 0	<1	<1	<1
Magnesium	ppm ASTM D5185m 1010	1078	1099	907
Calcium	ppm ASTM D5185m 1070	1200	1251	1100
Phosphorus	ppm ASTM D5185m 1150	1176	1192	959
Zinc	ppm ASTM D5185m 1270	1350	1476	1230
Sulfur	ppm ASTM D5185m 2060	3417	4015	3489

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >35	4	4	6
Sodium	ppm ASTM D5185m	2	5	19
Potassium	ppm ASTM D5185m >20	<1	30	0

INFRA-RED




method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >7.5	0.7	0.5	0.5
Nitration	Abs/cm *ASTM D7624 >20	7.3	9.6	7.9
Sulfation	Abs/.1mm *ASTM D7415 >30	19.5	20.1	19.4

FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	14.8	16.9	14.5
Base Number (BN)	mg KOH/g ASTM D2896 9.8	8.2	8.4	7.9







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	13.7	14.1	13.4

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0112959 **Received** : 04 Mar 2024
Lab Number : **06108025** **Tested** : 07 Mar 2024
Unique Number : 10911522 **Diagnosed** : 07 Mar 2024 - Jonathan Hester
Test Package : FLEET (Additional Tests: KV40)

GFL Environmental - 035 - Greensboro
 1236 Elon Place
 High Point, NC
 US 27263
 Contact: JORGE COSTA
 jorge.costa@gflenv.com
 T: (336)668-3712
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)