

OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



DT800 Component

Rear Axle

CHEVRON RPM SYNTHETIC GEAR 75W90 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Moor

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil


Fluid Condition

The condition of the oil is acceptable for the time in service.

(GAL)		Dec2021	Sep2022 Jan2023	Jan2023 Aug2023	Feb 2024	
SAMPLE INFOR	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0090324	PCA0102274	PCA0090278
Sample Date		Client Info		27 Feb 2024	16 Aug 2023	28 Jan 2023
Machine Age	mls	Client Info		178120	152234	101404
Oil Age	mls	Client Info		0	101404	101404
Oil Changed		Client Info		N/A	Changed	N/A
Sample Status				NORMAL	NORMAL	ABNORMAL
CONTAMINA	ΓΙΟΝ	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	NEG
WEAR METAI	_S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	45	112	85
Chromium	ppm	ASTM D5185m	>10	<1	<1	<1
Nickel	ppm	ASTM D5185m	>10	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	1	<1	1
Lead	ppm	ASTM D5185m	>25	2	0	0
Copper	ppm	ASTM D5185m	>50	0	<1	<1
Tin	ppm	ASTM D5185m	>10	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	<1	0
Cadmium		ASTM D5185m		0	0	0
	ppm		lii+/l			
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		195	242	222
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		13	18	18
Manganese	ppm	ASTM D5185m		<1	3	3
Magnesium	ppm	ASTM D5185m		107	96	88
Calcium	ppm	ASTM D5185m		242	201	190
Phosphorus	ppm	ASTM D5185m		1247	1311	1205
Zinc	ppm	ASTM D5185m		190	156	149
Sulfur	ppm	ASTM D5185m		19710	25056	23517
CONTAMINA	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>75	19	19	15
Sodium	ppm	ASTM D5185m		2	3	1
Potassium	ppm	ASTM D5185m	>20	0	0	0
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	NONE	▲ MODER
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
:21:44) Day: 1	Joalai	Violati		IILU		Pv: Poul Piddio





OIL ANALYSIS REPORT




FLUID PROF	PERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	110	86.7	85.5	85.7
SAMPLE IMA	AGES	method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image

GRAPHS









Certificate L2367

Laboratory Sample No.

Lab Number : 06109013 Unique Number: 10912510 Test Package : FLEET

: PCA0090324

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 05 Mar 2024 **Tested**

: 06 Mar 2024 Diagnosed : 06 Mar 2024 - Wes Davis

NW WHITE & CO - COLUMBIA DIVISION

100 INDEPENDENCE BLVD COLUMBIA, SC US 29210

Contact: GEORGE EDWARDS gedwards@nwwhite.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: NWWCOL [WUSCAR] 06109013 (Generated: 03/06/2024 13:31:44) Rev: 1

Submitted By: Paul Riddick

T:

F: