


# **OIL ANALYSIS REPORT**

## Sample Rating Trend







Machine Id DT752
Component Transmission (Auto)

COGNIS EMGARD 2805 ATF (--- QTS)

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the fluid.


## **Fluid Condition**

The condition of the fluid is acceptable for the time in service.

5 AIF ( QIS)  Mad2021 Aug2021 Onc2021 Mad2022 Sup2022 Mac2023 Aug2023 Feb2024								
SAMPLE INFOR	NOITAMS	method	limit/base	current	history1	history2		
Sample Number		Client Info		PCA0110895	PCA0104155	PCA0092564		
Sample Date		Client Info		20 Feb 2024	31 Aug 2023	30 Mar 2023		
Machine Age	mls	Client Info		226451	202039	151910		
Oil Age	mls	Client Info		127010	0	24900		
Oil Changed		Client Info		Changed	Not Changd	Not Changd		
Sample Status				NORMAL	NORMAL	NORMAL		
CONTAMINAT	ΓΙΟΝ	method	limit/base	current	history1	history2		
Water		WC Method	>0.1	NEG	NEG	NEG		
WEAR METAL	_S	method	limit/base	current	history1	history2		
Iron	ppm	ASTM D5185m	>220	78	65	53		
Chromium	ppm	ASTM D5185m	>2	0	0	<1		
Nickel	ppm	ASTM D5185m	>5	0	0	<1		
Titanium	ppm	ASTM D5185m		0	0	0		
Silver	ppm	ASTM D5185m	>5	0	0	0		
Aluminum	ppm	ASTM D5185m	>75	56	43	34		
Lead	ppm	ASTM D5185m	>95	26	22	19		
Copper	ppm	ASTM D5185m	>60	34	30	24		
Tin	ppm	ASTM D5185m	>10	2	2	1		
Vanadium	ppm	ASTM D5185m	7.0	0	0	0		
Cadmium	ppm	ASTM D5185m		0	0	0		
ADDITIVES		method	limit/base	current	history1	history2		
Boron	ppm	ASTM D5185m		96	109	111		
Barium	ppm	ASTM D5185m		0	7	0		
Molybdenum	ppm	ASTM D5185m		0	0	<1		
Manganese	ppm	ASTM D5185m		<1	<1	1		
Magnesium	ppm	ASTM D5185m		<1	4	0		
Calcium	ppm	ASTM D5185m		120	125	124		
Phosphorus	ppm	ASTM D5185m		268	271	299		
Zinc	ppm	ASTM D5185m		0	6	<1		
Sulfur	ppm	ASTM D5185m		1873	2151	2623		
CONTAMINA	NTS	method	limit/base	current	history1	history2		
Silicon	ppm	ASTM D5185m	>25	7	6	5		
Sodium	ppm	ASTM D5185m		6	4	4		
Potassium	ppm	ASTM D5185m	>20	<1	<1	<1		
VISUAL		method	limit/base	current	history1	history2		
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG		
Free Water	scalar	*Visual		NEG	NEG	NEG		





## **OIL ANALYSIS REPORT**




FLUID PROP	PERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	38.9	32.6	32.9	32.7
SAMPLE IMA	AGES	method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image

## **GRAPHS**









Certificate L2367

Laboratory Sample No.

: PCA0110895 Lab Number : 06109736 Unique Number: 10913233 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 05 Mar 2024 **Tested** 

: 06 Mar 2024 Diagnosed

: 06 Mar 2024 - Wes Davis

NW WHITE & CO - COLUMBIA DIVISION 100 INDEPENDENCE BLVD

COLUMBIA, SC US 29210

Contact: GEORGE EDWARDS gedwards@nwwhite.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: