


OIL ANALYSIS REPORT

Sample Rating Trend







Machine Id 4611M Component Diesel Engine Fluid PETRO CANADA DURON SHP 15W40 (36 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFOR	RMATION	method				history2
Sample Number		Client Info		GFL0104380	GFL0109974	GFL0110027
Sample Date		Client Info		04 Mar 2024	02 Feb 2024	02 Feb 2024
Machine Age	hrs	Client Info		21982	21742	21742
Oil Age	hrs	Client Info		600	600	600
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINA	TION	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR META	LS	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>90	7	7	12
Chromium	ppm	ASTM D5185m	>20	0	<1	<1
Nickel	ppm	ASTM D5185m	>2	0	0	0
Titanium	ppm	ASTM D5185m	>2	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>20	<1	2	2
Lead	ppm	ASTM D5185m	>40	0	0	0
Copper	ppm	ASTM D5185m	>330	0	0	<1
Tin	ppm	ASTM D5185m	>15	<1	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	5	2	2
Barium	ppm	ASTM D5185m	0	0	5	5
Molybdenum	ppm	ASTM D5185m	60	58	58	80
Manganese	ppm	ASTM D5185m	0	0	0	0
Magnesium	ppm	ASTM D5185m	1010	1034	914	1281
Calcium	ppm	ASTM D5185m	1070	1124	949	1261
Phosphorus	ppm	ASTM D5185m	1150	1169	875	1182
Zinc	ppm	ASTM D5185m	1270	1313	1176	1638
Sulfur	ppm	ASTM D5185m	2060	3340	2825	3828
CONTAMINA	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	3	5	4
Sodium	ppm	ASTM D5185m		33	0	3
Potassium	ppm	ASTM D5185m	>20	0	2	5
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>6	0.1	0	0.1
Nitration	Abs/cm	*ASTM D7624	>20	6.4	4.5	7.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.5	17.8	19.2
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.5	13.2	15.6
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.1	8.7	8.0



OIL ANALYSIS REPORT








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPERTIES		method				history2	
Visc @ 100°C	cSt	ASTM D445	15.4	14.0	14.2	13.6	

GRAPHS













Laboratory Sample No. Lab Number : 06109825

: GFL0104380

Unique Number : 10913322 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 06 Mar 2024

Tested : 07 Mar 2024 Diagnosed : 07 Mar 2024 - Wes Davis

GFL Environmental - 410 - Michigan West

39000 Van Born Rd Wayne, MI US 48184

Contact: Belal Dgheish bdgheish@gflenv.com T: (734)714-2340

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)