

OIL ANALYSIS REPORT

Sample Rating Trend





Differential

Fluid PETRO CANADA GEARLUBE TOS 80W90 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

				Mar2024		
SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0118500		
Sample Date		Client Info		01 Mar 2024		
Machine Age	hrs	Client Info		8072		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATI	ON	method	limit/base	current	history1	history2
Water		WC Method	>.2	NEG		
WEAR METALS	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	33		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m	>10	<1		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	2		
Lead	ppm	ASTM D5185m	>25	<1		
Copper	ppm	ASTM D5185m	>100	<1		
Tin	ppm	ASTM D5185m	>10	<1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	274	273		
Barium	ppm	ASTM D5185m	0.0	0		
Molybdenum	ppm	ASTM D5185m	0.0	<1		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m	5.5	1		
Calcium	ppm	ASTM D5185m	9.9	17		
Phosphorus	ppm	ASTM D5185m	855	901		
Zinc	ppm	ASTM D5185m	10	3		
Sulfur	ppm	ASTM D5185m	14849	18030		
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>75	7		
Sodium	ppm	ASTM D5185m		<1		
Potassium	ppm	ASTM D5185m	>20	1		
FLUID DEGRAD	ATIO <u>N</u>	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	1.5	1.79		




160 00 150


ත් 140

130 120 Abn

Marl

OIL ANALYSIS REPORT





Certificate L2367

Contact/Location: FRANK NALLY - SCRMIN