

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id DT853

Component Transmission (Auto) Fluid COGNIS EMGARD 2805 ATF (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the fluid.


Fluid Condition

The condition of the fluid is acceptable for the time in service.

Jun2023 0ct2023 Mar2024											
SAMPLE INFORM	NATION	method	limit/base	current	history1	history2					
Sample Number		Client Info		PCA0111603	PCA0101843	PCA0095260					
Sample Date		Client Info		01 Mar 2024	31 Oct 2023	26 Jun 2023					
Machine Age	mls	Client Info		0	0	0					
Oil Age	mls	Client Info		0	0	0					
Oil Changed		Client Info		N/A	N/A	N/A					
Sample Status				NORMAL	NORMAL	NORMAL					
CONTAMINATI	ON	method	limit/base	current	history1	history2					
Water		WC Method	>0.1	NEG	NEG	NEG					
WEAR METALS	S	method	limit/base	current	history1	history2					
Iron	ppm	ASTM D5185m	>160	20	27	13					
Chromium	ppm	ASTM D5185m	>5	0	0	0					
Nickel	ppm	ASTM D5185m	>5	0	<1	0					
Titanium	ppm	ASTM D5185m		0	0	<1					
Silver	ppm	ASTM D5185m	>5	0	0	0					
Aluminum	ppm	ASTM D5185m	>50	6	8	4					
Lead	ppm	ASTM D5185m	>50	<1	2	2					
Copper	ppm	ASTM D5185m	>225	5	8	5					
Tin	ppm	ASTM D5185m	>10	<1	1	0					
Vanadium	ppm	ASTM D5185m		0	0	<1					
Cadmium	ppm	ASTM D5185m		0	0	0					
ADDITIVES		method	limit/base	current	history1	history2					
Boron	ppm	ASTM D5185m		92	72	87					
Barium	ppm	ASTM D5185m		0	0	0					
Molybdenum	ppm	ASTM D5185m		1	0	<1					
Manganese	ppm	ASTM D5185m		0	<1	<1					
Magnesium	ppm	ASTM D5185m		11	3	1					
Calcium	ppm	ASTM D5185m		162	121	125					
Phosphorus	ppm	ASTM D5185m		265	210	217					
Zinc	ppm	ASTM D5185m		40	0	<1					
Sulfur	ppm	ASTM D5185m		1889	1645	1873					
CONTAMINAN	TS	method	limit/base	current	history1	history2					
Silicon	ppm	ASTM D5185m	>20	3	3	3					
Sodium	ppm	ASTM D5185m		3	4	4					
Potassium	ppm	ASTM D5185m	>20	0	1	0					
VISUAL		method	limit/base	current	history1	history2					
White Metal	scalar	*Visual	NONE	NONE	NONE	LIGHT					
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE					
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE					
Silt	scalar	*Visual	NONE	NONE	NONE	NONE					
Debris	scalar	*Visual	NONE	NONE	NONE	NONE					
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE					
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML					
Odor	scalar	*Visual	NORML	NORML	NORML	NORML					
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG					
Free Water	scalar	*Visual		NEG	NEG	NEG					
4:38:31) Rev: 1					Submitted By	: DAVID WEBB					



OIL ANALYSIS REPORT



	FLUID PROPI Visc @ 40°C		method ASTM D445	limit/base 38.9	current 32.4	history1 30.14	history 31.0
	SAMPLE IMA		method	limit/base	current	history1	history
	SAIVIF LE IIVIA	GES	methou	IIIIII/Dase	current	Thistory I	TIIStOLY
	Color				no imore	na ima na	
	COIOI				no image	no image	no image
Mar1/24							
2	Bottom				no image	no image	no image
							Ū
	GRAPHS						
	Ferrous Alloys						
	30 iron	\sim					
	25 - nickel						
	20-						
	툍 15						
	10-						
	5						
	Jun 26/23	0ct31/23		Mar1/24			
	Jun2	0ct3		Mar			
	Non-ferrous Meta	als					
	9- copper						
	8 - tin						
	6						
	ug 5-						
	4						
	2-						
		and in the local division of the local divis	in minute and a set of a set of the set of t	17424948			
	Jun26/23	0ct31/23		Mar1/24			
				W			
	Viscosity @ 40°C	;					
	Abnormal 42						
	40 Base						
	38- 						
	성 						
	34						
	32 - Abnormal						
	30						
	28	1/23 -		Mar1/24			
	Jun26/23	0ct31/23		Mar			
Laboratory	: WearCheck USA - 5	01 Madison	Ave., Carv	NC 27513	NW WH	IITE & CO - BEAU	FORT DIVIS
Sample No.	: PCA0111603	Receiv	ed : 06	Mar 2024		1491 YENMASS	SEE HIGHW
Lab Number Unique Number		Tested Diagno		Mar 2024 Mar 2024 - We	es Davie	V	ARNVILLE, US 29
367 Test Package	: FLEET	-			55 0 4 1 1 5	Contact: VINCI	
	, contact Customer Ser					bullockvince5	