


OIL ANALYSIS REPORT

Sample Rating Trend







Machine Id DT852

Component

Front Differential

CHEVRON DELO SYNTHETIC GEAR 75W90 (--- QTS

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The condition of the oil is acceptable for the time in service.


n (OTC)						
0 (QTS)		Dec2022	Mar2023	Jul2023 Oct2023	Mar2024	
SAMPLE INFOR	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0111606	PCA0101816	PCA0095265
Sample Date		Client Info		01 Mar 2024	25 Oct 2023	05 Jul 2023
Machine Age	mls	Client Info		25000	25000	25000
Oil Age	mls	Client Info		25000	25000	25000
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINA	TION	method	limit/base	current	history1	history2
Water		WC Method	>.2	NEG	NEG	NEG
WEAR METAI	LS	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	92	81	145
Chromium	ppm	ASTM D5185m	>10	0	0	<1
Nickel	ppm	ASTM D5185m	>10	0	0	<1
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	0	0	<1
Lead	ppm	ASTM D5185m	>25	0	0	0
Copper	ppm	ASTM D5185m	>100	9	8	42
Tin	ppm	ASTM D5185m	>10	0	0	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		231	215	296
Barium	ppm	ASTM D5185m		1	0	0
Molybdenum	ppm	ASTM D5185m		17	17	<1
Manganese	ppm	ASTM D5185m		4	4	13
Magnesium	ppm	ASTM D5185m		91	87	1
Calcium	ppm	ASTM D5185m		196	184	7
Phosphorus	ppm	ASTM D5185m		1312	1272	1435
Zinc	ppm	ASTM D5185m		155	154	11
Sulfur	ppm	ASTM D5185m		19031	20875	25056
CONTAMINA	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>75	9	11	22
Sodium	ppm	ASTM D5185m		2	2	5
Potassium	ppm	ASTM D5185m	>20	0	1	2
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
.20.01\ Day: 1					Cubmitted D.	" D V / I D / W / C D I





OIL ANALYSIS REPORT



FLUID PROPI	ERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	106	83.8	83.7	102
SAMPLE IMA	GES	method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image









Certificate L2367

Laboratory Sample No.

: PCA0111606 Lab Number : 06110547 Unique Number : 10914044 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received **Tested**

: 06 Mar 2024 : 07 Mar 2024 Diagnosed : 07 Mar 2024 - Wes Davis

NW WHITE & CO - BEAUFORT DIVISION 1491 YENMASSEE HIGHWAY

VARNVILLE, SC US 29944

Contact: DAVID WEBB 63DAVIDWDAVID@GMAIL.COM

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (864)973-1607 F: