


# **OIL ANALYSIS REPORT**

### Sample Rating Trend









Machine Id DT853 Component **Rear Differential** 

CHEVRON DELO SYNTHET

# DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the


### **Fluid Condition**

The condition of the oil is acceptable for the time in service.

TIC GEAR 75W90	( QTS)	Ju	n2023	Oct2023 Mar20	24	
SAMPLE INFOR	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0111601	PCA0101821	PCA0095258
Sample Date		Client Info		01 Mar 2024	31 Oct 2023	26 Jun 2023
Machine Age	mls	Client Info		0	0	0
Oil Age	mls	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ΓΙΟΝ	method	limit/base	current	history1	history2
Water		WC Method	>.2	NEG	NEG	NEG
WEAR METAL	_S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>1200	64	126	121
Chromium	ppm	ASTM D5185m	>8	0	1	1
Nickel	ppm	ASTM D5185m	>20	0	<1	<1
Titanium	ppm	ASTM D5185m	>4	0	<1	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>30	1	2	2
Lead	ppm	ASTM D5185m	>25	0	0	0
Copper	ppm	ASTM D5185m	>50	0	0	1
Tin	ppm	ASTM D5185m	>5	0	<1	0
Vanadium	ppm	ASTM D5185m		0	0	<1
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		260	284	301
Barium	ppm	ASTM D5185m		<1	2	0
Molybdenum	ppm	ASTM D5185m		8	0	<1
Manganese	ppm	ASTM D5185m		1	5	4
Magnesium	ppm	ASTM D5185m		50	4	2
Calcium	ppm	ASTM D5185m		98	11	11
Phosphorus	ppm	ASTM D5185m		1365	1557	1420
Zinc	ppm	ASTM D5185m		81	13	13
Sulfur	ppm	ASTM D5185m		21567	26381	25056
CONTAMINA	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>230	20	21	16
Sodium	ppm	ASTM D5185m		2	8	8
Potassium	ppm	ASTM D5185m	>20	0	2	0
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG





# **OIL ANALYSIS REPORT**




FLUID PROF	PERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	106	91.9	98.2	98.5
SAMPLE IMA	AGES	method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image

## **GRAPHS**











Laboratory Sample No.

: PCA0111601 Lab Number : 06110550 Unique Number : 10914047

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received **Tested** 

Diagnosed

: 06 Mar 2024 : 07 Mar 2024 : 07 Mar 2024 - Wes Davis

NW WHITE & CO - BEAUFORT DIVISION

1491 YENMASSEE HIGHWAY VARNVILLE, SC

US 29944 Contact: VINCENT BULLOCK bullockvince514@gmail.com

Test Package : FLEET Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: NWWVAR [WUSCAR] 06110550 (Generated: 03/07/2024 14:38:20) Rev: 1

T:

F: