

# **OIL ANALYSIS REPORT**

# (ECY338) **AUTOCAR 3742**

Component **Diesel Engine** 

PETRO CANADA DURON SHP 15W40 (10 GAL)

Sample Rating Trend



### DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the


### **Fluid Condition**


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

		32017 Nov201	7 Oct2018 Oct2019	Jun2020 Feb2021 Sep2021 S	iep2023	
SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0109030	GFL0109043	GFL0109071
Sample Date		Client Info		29 Feb 2024	22 Feb 2024	07 Feb 2024
Machine Age	nrs	Client Info		18630	18589	18438
Oil Age	hrs	Client Info		2888	18589	2696
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATIO	N	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron p	opm	ASTM D5185m	>165	23	26	18
Chromium	opm	ASTM D5185m	>5	1	3	2
Nickel	opm	ASTM D5185m	>4	0	<1	0
Titanium	opm	ASTM D5185m	>2	<1	<1	<1
	opm	ASTM D5185m	>2	0	0	0
	opm	ASTM D5185m	>20	3	1	<1
	opm	ASTM D5185m	>150	0	<1	0
·	opm	ASTM D5185m	>90	1	2	<1
	opm		>5	0	<1	<1
	opm	ASTM D5185m		<1	<1	<1
	opm	ASTM D5185m		0	<1	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	opm	ASTM D5185m	0	8	13	16
·	opm	ASTM D5185m	0	0	1	0
	opm	ASTM D5185m	60	54	57	62
	opm	ASTM D5185m	0	0	<1	<1
	opm	ASTM D5185m	1010	702	686	779
	opm	ASTM D5185m	1070	1122	1020	1153
	opm	ASTM D5185m	1150	636	892	977
	opm	ASTM D5185m	1270	1125	1072	1139
	opm	ASTM D5185m	2060	2648	3066	2942
CONTAMINANT	S	method	limit/base	current	history1	history2
Silicon	opm	ASTM D5185m	>35	3	6	4
Sodium	opm	ASTM D5185m		4	3	4
Potassium	opm	ASTM D5185m	>20	3	2	0
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>7.5	1	0.9	0.7
	Abs/cm	*ASTM D7624	>20	7.8	7.3	6.6
	Abs/.1mm	*ASTM D7415		18.9	18.9	18.2
FLUID DEGRADA	MOITA	method	limit/base	current	history1	history2
Oxidation /	Abs/.1mm	*ASTM D7414	>25	13.3	12.7	12.5
	ng KOH/g	ASTM D2896	9.8	7.7	7.7	7.9
= 3.30 · (2.11)			0			



## **OIL ANALYSIS REPORT**








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
<b>Emulsified Water</b>	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPI	ERTIES	method				history2
Visc @ 100°C	cSt	ASTM D445	15.4	12.5	12.7	12.5

### **GRAPHS**













Certificate L2367

Laboratory Sample No.

Lab Number : 06111136 Unique Number : 10914633

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0109030

Test Package : FLEET

Received : 07 Mar 2024 **Tested** 

: 07 Mar 2024 Diagnosed : 07 Mar 2024 - Wes Davis

GFL Environmental - 009 - Fairburn 6905 Roosevelt Hwy

Fairburn, GA US 30213 Contact: Eric Jones

erjones@gflenv.com T: (678)630-9927

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: GFL009 [WUSCAR] 06111136 (Generated: 03/07/2024 17:42:18) Rev: 1