


# OIL ANALYSIS REPORT

Sample Rating Trend

**NORMAL**



Machine Id  
**2126957**

Component  
**Diesel Engine**

Fluid  
**PETRO CANADA DURON SHP 10W30 (--- QTS)**

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			<b>PCA0115471</b>	PCA0081423	---
Sample Date	Client Info			<b>06 Mar 2024</b>	17 Oct 2023	---
Machine Age	mls	Client Info		<b>186879</b>	158989	---
Oil Age	mls	Client Info		<b>0</b>	0	---
Oil Changed	Client Info			<b>N/A</b>	N/A	---
Sample Status				<b>NORMAL</b>	NORMAL	---

CONTAMINATION		method	limit/base	current	history1	history2
Fuel	WC Method	>5		<b>&lt;1.0</b>	<1.0	---
Water	WC Method	>0.2		<b>NEG</b>	NEG	---
Glycol	WC Method			<b>NEG</b>	NEG	---

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	<b>25</b>	58	---
Chromium	ppm	ASTM D5185m	>20	<b>&lt;1</b>	<1	---
Nickel	ppm	ASTM D5185m	>4	<b>3</b>	1	---
Titanium	ppm	ASTM D5185m		<b>&lt;1</b>	0	---
Silver	ppm	ASTM D5185m	>3	<b>&lt;1</b>	0	---
Aluminum	ppm	ASTM D5185m	>20	<b>4</b>	6	---
Lead	ppm	ASTM D5185m	>40	<b>&lt;1</b>	3	---
Copper	ppm	ASTM D5185m	>330	<b>15</b>	39	---
Tin	ppm	ASTM D5185m	>15	<b>&lt;1</b>	2	---
Vanadium	ppm	ASTM D5185m		<b>0</b>	0	---
Cadmium	ppm	ASTM D5185m		<b>0</b>	0	---



ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	<b>&lt;1</b>	2	---
Barium	ppm	ASTM D5185m	0	<b>0</b>	0	---
Molybdenum	ppm	ASTM D5185m	50	<b>60</b>	67	---
Manganese	ppm	ASTM D5185m	0	<b>0</b>	1	---
Magnesium	ppm	ASTM D5185m	950	<b>943</b>	908	---
Calcium	ppm	ASTM D5185m	1050	<b>1092</b>	1146	---
Phosphorus	ppm	ASTM D5185m	995	<b>1032</b>	955	---
Zinc	ppm	ASTM D5185m	1180	<b>1260</b>	1224	---
Sulfur	ppm	ASTM D5185m	2600	<b>3235</b>	2596	---

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<b>7</b>	10	---
Sodium	ppm	ASTM D5185m		<b>1</b>	0	---
Potassium	ppm	ASTM D5185m	>20	<b>7</b>	16	---

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	<b>0.5</b>	0.8	---
Nitration	Abs/cm	*ASTM D7624	>20	<b>10.3</b>	12.8	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>21.1</b>	24.7	---

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>19.0</b>	23.3	---
Base Number (BN)	mg KOH/g	ASTM D2896		<b>6.7</b>	3.8	---





# OIL ANALYSIS REPORT



PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.2	---

## GRAPHS



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : PCA0115471      **Received** : 07 Mar 2024  
**Lab Number** : 06111189      **Tested** : 07 Mar 2024  
**Unique Number** : 10914686      **Diagnosed** : 07 Mar 2024 - Wes Davis  
**Test Package** : FLEET

**PERDUE FARMS - PRINCE GEORGE**  
 6012 HARDWARE DR  
 PRINCE GEORGE, VA  
 US 23875  
 Contact: MICHAEL DAVIS  
 MICHAELP.DAVIS@PERDUE.COM

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
F: