




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
424019-856

Component
Diesel Engine

Fluid
PETRO CANADA DURON HP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	GFL0115449	GFL0062212	GFL0062187
Sample Date	Client Info	29 Feb 2024	01 Aug 2023	25 Jun 2023
Machine Age	hrs	17293	17293	17075
Oil Age	hrs	500	820	360
Oil Changed	Client Info	Not Changed	Changed	Not Changed
Sample Status		NORMAL	NORMAL	NORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >5	<1.0	<1.0	<1.0
Water	WC Method >0.2	NEG	NEG	NEG
Glycol	WC Method	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >100	43	35	24
Chromium	ppm ASTM D5185m >20	<1	1	<1
Nickel	ppm ASTM D5185m >4	0	0	0
Titanium	ppm ASTM D5185m	0	<1	0
Silver	ppm ASTM D5185m >3	0	<1	0
Aluminum	ppm ASTM D5185m >20	6	4	4
Lead	ppm ASTM D5185m >40	0	2	0
Copper	ppm ASTM D5185m >330	1	2	1
Tin	ppm ASTM D5185m >15	0	<1	<1
Vanadium	ppm ASTM D5185m	<1	<1	0
Cadmium	ppm ASTM D5185m	0	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m	9	6	8
Barium	ppm ASTM D5185m	0	0	0
Molybdenum	ppm ASTM D5185m	76	67	66
Manganese	ppm ASTM D5185m	<1	<1	<1
Magnesium	ppm ASTM D5185m	985	1048	1014
Calcium	ppm ASTM D5185m	1278	1280	1214
Phosphorus	ppm ASTM D5185m	1002	1115	1092
Zinc	ppm ASTM D5185m	1229	1381	1360
Sulfur	ppm ASTM D5185m	2873	3527	3698

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >25	11	17	21
Sodium	ppm ASTM D5185m	6	4	2
Potassium	ppm ASTM D5185m >20	7	6	4

INFRA-RED



method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >3	2.1	1.4	1.2
Nitration	Abs/cm *ASTM D7624 >20	13.1	10.9	9.7
Sulfation	Abs/.1mm *ASTM D7415 >30	25.6	23.3	22.7

FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	19.0	18.6	18.3
Base Number (BN)	mg KOH/g ASTM D2896 9.8	7.2	7.6	8.1







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.6	13.8	14.6	14.3

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0115449 **Received** : 07 Mar 2024
Lab Number : 06111233 **Tested** : 08 Mar 2024
Unique Number : 10914730 **Diagnosed** : 08 Mar 2024 - Wes Davis
Test Package : FLEET

GFL Environmental - 626 - Cadillac Hauling
 1501 Ron Wilson St
 Cadillac, MI
 US 49601
 Contact: GARY BREWER
 gbrewerjr@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)