


# **OIL ANALYSIS REPORT**

# (P922180) Preferred Service-Tractor [Preferred Service-Tractor] 192A01004

**Diesel Engine** 

PETRO CANADA DURON UHP 5W30 (36 QTS)





# DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the


### **Fluid Condition**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

) (S)			Nov2023	Mar2024		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0116681	PCA0109409	
Sample Date		Client Info		05 Mar 2024	01 Nov 2023	
Machine Age	mls	Client Info		520890	501261	
Oil Age	mls	Client Info		19629	18235	
Oil Changed		Client Info		Changed	Changed	
Sample Status				NORMAL	NORMAL	
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>6.0	<1.0	<1.0	
Water		WC Method	>0.2	NEG	NEG	
Glycol		WC Method		NEG	NEG	
WEAR METAL	_S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	34	39	
Chromium	ppm	ASTM D5185m	>20	<1	<1	
Nickel	ppm	ASTM D5185m	>2	<1	<1	
Titanium	ppm	ASTM D5185m		<1	<1	
Silver	ppm	ASTM D5185m	>2	<1	<1	
Aluminum	ppm	ASTM D5185m	>25	3	3	
Lead	ppm	ASTM D5185m	>40	2	2	
Copper	ppm	ASTM D5185m	>330	2	2	
Tin	ppm	ASTM D5185m	>15	<1	<1	
Vanadium	ppm	ASTM D5185m		<1	<1	
Cadmium	ppm	ASTM D5185m		<1	<1	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	0	
Barium	ppm	ASTM D5185m	0	0	0	
Molybdenum	ppm	ASTM D5185m	64	64	73	
Manganese	ppm	ASTM D5185m	0	<1	<1	
Magnesium	ppm	ASTM D5185m	1160	1006	1127	
Calcium	ppm	ASTM D5185m	820	1118	1252	
Phosphorus	ppm	ASTM D5185m	1160	1141	1196	
Zinc	ppm	ASTM D5185m	1260	1286	1450	
Sulfur	ppm	ASTM D5185m	3000	3126	3091	
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	5	5	
Sodium	ppm	ASTM D5185m		2	3	
Potassium	ppm	ASTM D5185m	>20	2	3	
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	1	1.5	
Nitration	Abs/cm	*ASTM D7624	>20	9.3	9.4	
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.8	22.6	
FLUID DEGRADATION method limit/base current history1 history2						
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.5	17.3	
Base Number (BN)	mg KOH/g	ASTM D2896	11.0	6.2	7.0	
. ,						




# **OIL ANALYSIS REPORT**





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
<b>Emulsified Water</b>	scalar	*Visual	>0.2	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	


FLUID PROPE	RHES	method				history2
Visc @ 100°C	cSt	ASTM D445	11.9	11.2	11.3	

## **GRAPHS**













Certificate L2367

Laboratory Sample No.

: PCA0116681 Lab Number : 06114033 Unique Number : 10922866 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 11 Mar 2024 : 12 Mar 2024 **Tested** Diagnosed

: 12 Mar 2024 - Wes Davis

Transervice - Shop 1920 - Preferred Service 1955 W. North Avenue, Bldg K

Melrose Park, IL US 60160

Contact: Tom Lindeman tlindemann@transervice.com T: (630)376-8946

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)