


OIL ANALYSIS REPORT

(P798347) Preferred Service-Tractor [Preferred Service-Tractor] 192A01987

Diesel Engine

PETRO CANADA DURON SHP 10W30 (36 QTS)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

QIS)			Nov2023	Feb 2024		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0116686	PCA0109418	
Sample Date		Client Info		29 Feb 2024	06 Nov 2023	
Machine Age	mls	Client Info		412517	395852	
Oil Age	mls	Client Info		395852	18142	
Oil Changed		Client Info		Changed	Changed	
Sample Status				NORMAL	NORMAL	
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>6.0	<1.0	<1.0	
Water		WC Method	>0.2	NEG	NEG	
Glycol		WC Method		NEG	NEG	
WEAR METAL	_S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	25	24	
Chromium	ppm	ASTM D5185m	>20	<1	<1	
Nickel	ppm	ASTM D5185m	>2	<1	<1	
Titanium	ppm	ASTM D5185m		<1	<1	
Silver	ppm	ASTM D5185m	>2	<1	<1	
Aluminum	ppm	ASTM D5185m	>25	5	3	
Lead	ppm	ASTM D5185m	>40	2	2	
Copper	ppm	ASTM D5185m	>330	6	3	
Tin	ppm	ASTM D5185m	>15	2	<1	
Vanadium	ppm	ASTM D5185m		<1	<1	
Cadmium	ppm	ASTM D5185m		<1	<1	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	<1	0	
Barium	ppm	ASTM D5185m	0	0	0	
Molybdenum	ppm	ASTM D5185m	50	63	60	
Manganese	ppm	ASTM D5185m	0	<1	<1	
Magnesium	ppm	ASTM D5185m	950	1006	923	
Calcium	ppm	ASTM D5185m	1050	1104	1053	
Phosphorus	ppm	ASTM D5185m	995	1137	980	
Zinc	ppm	ASTM D5185m	1180	1290	1198	
Sulfur	ppm	ASTM D5185m	2600	3310	2862	
CONTAMINAN	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	5	4	
Sodium	ppm	ASTM D5185m		1	<1	
Potassium	ppm	ASTM D5185m	>20	4	3	
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.9	1.1	
Nitration	Abs/cm	*ASTM D7624	>20	8.9	8.9	
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.9	21.4	
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.1	16.5	
Base Number (BN)	mg KOH/g	ASTM D2896		6.7	7.0	



OIL ANALYSIS REPORT



VISUAL		method				history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	
ELLUD BBOBE	DTIES					

14 Abnom	nal					
4		 	 	 	 	
13						
Base						
12 - Base		 	 	 	 	
11-		 	 	 	 	
10						
Abnom	nal					
9 -		 	 			

Visc @ 100°C **GRAPHS**


cSt

ASTM D445 12.00


11.2


11.3

Ferrous Alloys



	Non-ferrous Metals	
8.1	copper	
6 - wdd		-
2 - EC/gnoN	57/00/00	Feb29/24
١.	Viscosity @ 1000C	







Certificate L2367

Laboratory Sample No. Lab Number : 06114037 Unique Number : 10922870

Test Package : FLEET

: PCA0116686

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received

Tested Diagnosed

: 11 Mar 2024 : 12 Mar 2024

: 12 Mar 2024 - Wes Davis

Transervice - Shop 1920 - Preferred Service 1955 W. North Avenue, Bldg K

Melrose Park, IL US 60160

Contact: Tom Lindeman tlindemann@transervice.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (630)376-8946