


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
(51456Z) Walgreens - Tractor
Machine Id
[Walgreens - Tractor] 136A63326
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 10W30 (11 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	PCA0103560	PCA0103488	PCA0094981
Sample Date	Client Info	21 Feb 2024	11 Dec 2023	17 Aug 2023
Machine Age	mls Client Info	206969	176273	143182
Oil Age	mls Client Info	60000	33111	67114
Oil Changed	Client Info	Changed	Not Changd	N/A
Sample Status		NORMAL	NORMAL	NORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >5	<1.0	<1.0	<1.0
Water	WC Method >0.2	NEG	NEG	NEG
Glycol	WC Method	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >80	33	17	26
Chromium	ppm ASTM D5185m >5	2	2	3
Nickel	ppm ASTM D5185m >2	0	0	0
Titanium	ppm ASTM D5185m	0	0	0
Silver	ppm ASTM D5185m >3	0	<1	0
Aluminum	ppm ASTM D5185m >30	17	11	25
Lead	ppm ASTM D5185m >30	0	0	0
Copper	ppm ASTM D5185m >150	32	31	46
Tin	ppm ASTM D5185m >5	0	<1	<1
Vanadium	ppm ASTM D5185m	0	0	<1
Cadmium	ppm ASTM D5185m	0	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 2	<1	1	0
Barium	ppm ASTM D5185m 0	0	0	0
Molybdenum	ppm ASTM D5185m 50	53	58	57
Manganese	ppm ASTM D5185m 0	<1	1	<1
Magnesium	ppm ASTM D5185m 950	885	964	923
Calcium	ppm ASTM D5185m 1050	1041	1083	1142
Phosphorus	ppm ASTM D5185m 995	840	1018	883
Zinc	ppm ASTM D5185m 1180	1048	1285	1179
Sulfur	ppm ASTM D5185m 2600	2333	2614	2497

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >20	6	5	5
Sodium	ppm ASTM D5185m	2	3	3
Potassium	ppm ASTM D5185m >20	31	19	60



INFRA-RED

method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >3	1	0.6	1
Nitration	Abs/cm *ASTM D7624 >20	10.8	8.5	9.1
Sulfation	Abs/.1mm *ASTM D7415 >30	23.9	21.7	26.3

FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	22.4	18.7	24.9
Base Number (BN)	mg KOH/g ASTM D2896	4.8	6.7	5.7





OIL ANALYSIS REPORT



PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

PARAMETER	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.8	11.6

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
 Sample No. : PCA0103560
 Lab Number : 06114831
 Unique Number : 10923664
 Test Package : FLEET
 Received : 11 Mar 2024
 Tested : 12 Mar 2024
 Diagnosed : 12 Mar 2024 - Wes Davis

Transervice - Shop 1369 - Berkeley-Waxahachie
 710 Ovilla Road
 Waxahachie, TX
 US 75167
 Contact: Robert Beal
 rbeal@transervice.com
 T: (972)923-9928
 F: (972)923-9919

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)