

OIL ANALYSIS REPORT

Sample Rating Trend







Machine Id 746000

Component Natural Gas Engine

PETRO CANADA DURON GEO LD 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

Metal levels are typical for a components first oil change.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0098084		
Sample Date		Client Info		06 Mar 2024		
Machine Age	hrs	Client Info		225		
Oil Age	hrs	Client Info		225		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINAT	ION	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	3		
Chromium	ppm	ASTM D5185m	>4	0		
Nickel	ppm	ASTM D5185m	>2	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m	>3	0		
Aluminum	ppm	ASTM D5185m	>9	<1		
Lead	ppm	ASTM D5185m	>30	0		
Copper	ppm	ASTM D5185m	>35	<1		
Tin	ppm	ASTM D5185m	>4	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	50	34		
Barium	ppm	ASTM D5185m	5	0		
Molybdenum	ppm	ASTM D5185m	50	49		
Manganese	ppm	ASTM D5185m	0	0		
Magnesium	ppm	ASTM D5185m	560	748		
Calcium	ppm	ASTM D5185m	1510	1252		
Phosphorus	ppm	ASTM D5185m	780	750		
Zinc	ppm	ASTM D5185m	870	872		
Sulfur	ppm	ASTM D5185m	2040	2679		
CONTAMINAN						
CONTAIMINAN	TS	method	limit/base	current	history1	history2
Silicon	TS ppm	method ASTM D5185m	limit/base >+100	current 40	history1	history2
Silicon	ppm	ASTM D5185m	>+100	40		
Silicon Sodium	ppm ppm	ASTM D5185m ASTM D5185m	>+100	40 4		
Silicon Sodium Potassium	ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m	>+100 >20	40 4 0		
Silicon Sodium Potassium INFRA-RED	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m method	>+100 >20 limit/base	40 4 0 current	 history1	 history2
Silicon Sodium Potassium INFRA-RED Soot %	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m method *ASTM D7844	>+100 >20 limit/base	40 4 0 current 0	 history1	 history2
Silicon Sodium Potassium INFRA-RED Soot % Nitration	ppm ppm ppm % Abs/cm Abs/.1mm	ASTM D5185m ASTM D5185m ASTM D5185m method *ASTM D7844 *ASTM D7624	>+100 >20 limit/base >20	40 4 0 current 0 8.3	 history1 	 history2
Silicon Sodium Potassium INFRA-RED Soot % Nitration Sulfation	ppm ppm ppm % Abs/cm Abs/.1mm	ASTM D5185m ASTM D5185m ASTM D5185m method *ASTM D7844 *ASTM D7624 *ASTM D7415	>+100 >20 limit/base >20 >30	40 4 0 current 0 8.3 20.0	 history1 	 history2
Silicon Sodium Potassium INFRA-RED Soot % Nitration Sulfation FLUID DEGRAD	ppm ppm ppm % Abs/cm Abs/cm Abs/1mm	ASTM D5185m ASTM D5185m ASTM D5185m *ASTM D7844 *ASTM D7844 *ASTM D7624 *ASTM D7415	>+100 >20 limit/base >20 >30 limit/base	40 4 0 current 0 8.3 20.0 current	 history1 history1	 history2 history2




OIL ANALYSIS REPORT

VISUAL







Report Id: GFL932 [WUSCAR] 06115649 (Generated: 03/13/2024 14:38:27) Rev: 1

Certificate L2367

Submitted By: GFL932, GFL414 - BECKY FLETCHER