

OIL ANALYSIS REPORT

Sample Rating Trend







Machine Id **T328** Component **Diesel Engine** Fluid {not provided} (--- QTS)

DIAGNOSIS

Recommendation

Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

Metal levels are typical for a new component breaking in.

Contamination

Fuel content negligible. Elevated aluminum (AI) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

| SAMPLE INFORM | NATION | method | limit/base | current | history1 | history2 |
|------------------|---------------|-------------|------------|-------------|----------|----------|
| Sample Number | | Client Info | | PCA0119947 | | |
| Sample Date | | Client Info | | 06 Mar 2024 | | |
| Machine Age | mls | Client Info | | 25871 | | |
| Oil Age | mls | Client Info | | 0 | | |
| Oil Changed | | Client Info | | Changed | | |
| Sample Status | | | | NORMAL | | |
| CONTAMINATI | ON | method | limit/base | current | history1 | history2 |
| Water | | WC Method | >0.2 | NEG | | |
| Glycol | | WC Method | | NEG | | |
| WEAR METALS | S | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >100 | 68 | | |
| Chromium | ppm | ASTM D5185m | >20 | <1 | | |
| Nickel | ppm | ASTM D5185m | >4 | 0 | | |
| Titanium | ppm | ASTM D5185m | | <1 | | |
| Silver | ppm | ASTM D5185m | >3 | <1 | | |
| Aluminum | ppm | ASTM D5185m | >20 | 35 | | |
| Lead | ppm | ASTM D5185m | >40 | <1 | | |
| Copper | ppm | ASTM D5185m | >330 | 25 | | |
| Tin | ppm | ASTM D5185m | >15 | 2 | | |
| Vanadium | ppm | ASTM D5185m | | 0 | | |
| Cadmium | ppm | ASTM D5185m | | 0 | | |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | | 20 | | |
| Barium | ppm | ASTM D5185m | | 0 | | |
| Molybdenum | ppm | ASTM D5185m | | 13 | | |
| Manganese | ppm | ASTM D5185m | | 2 | | |
| Magnesium | ppm | ASTM D5185m | | 804 | | |
| Calcium | ppm | ASTM D5185m | | 1334 | | |
| Phosphorus | ppm | ASTM D5185m | | 806 | | |
| Zinc | ppm | ASTM D5185m | | 963 | | |
| Sulfur | ppm | ASTM D5185m | | 3138 | | |
| CONTAMINAN | TS | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >25 | 13 | | |
| Sodium | ppm | ASTM D5185m | | 3 | | |
| Potassium | ppm | ASTM D5185m | >20 | 106 | | |
| Fuel | % | ASTM D3524 | >5 | 0.4 | | |
| INFRA-RED | | method | limit/base | current | history1 | history2 |
| Soot % | % | *ASTM D7844 | >3 | 0.4 | | |
| Nitration | Abs/cm | *ASTM D7624 | >20 | 11.3 | | |
| Sulfation | Abs/.1mm | *ASTM D7415 | >30 | 25.6 | | |
| FLUID DEGRAD | ATION | method | limit/base | current | history1 | history2 |
| Oxidation | Abs/.1mm | *ASTM D7414 | >25 | 21.7 | | |
| Base Number (BN) | mg KOH/g | ASTM D2896 | | 4.7 | | |
| | | | | | | |




OIL ANALYSIS REPORT









VISUAL *Visual NONE NONE White Metal scalar Yellow Metal *Visual NONE NONE scalar Precipitate scalar *Visual NONE NONE Silt scalar *Visual NONE NONE Debris *Visual NONE NONE scalar Sand/Dirt NONE scalar *Visual NONE NORML Appearance *Visual NORML scalar Odor *Visual NORML NORML scalar **Emulsified Water** scalar *Visual >0.2 NEG Free Water scalar *Visual NEG **FLUID PROPERTIES** Visc @ 100°C cSt ASTM D445 11.8 GRAPHS Ferrous Alloys 70 60 nicke 50 40 20 10 n. Aar6/24 Non-ferrous Metals 2 lead 20 15

Base Number

5.

____4 HU

2 3.0

. g 2.0

0.0

Aar6/24

Base

Mar6/24

: 12 Mar 2024

: 14 Mar 2024



: 14 Mar 2024 - Sean Felton Unique Number : 10924550 Diagnosed Test Package : FLEET (Additional Tests: FuelDilution, PercentFuel) Contact: GEORGE EDWARDS Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. gedwards@nwwhite.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received

Tested

Viscosity @ 100°C

18

16

() 0-001 14

53 13

12

11 10

: PCA0119947

Laboratory

Sample No.

Lab Number : 06115717

NW WHITE & CO - COLUMBIA DIVISION

100 INDEPENDENCE BLVD

COLUMBIA, SC

US 29210

T:

F: