


# **OIL ANALYSIS REPORT**

Sample Rating Trend



NORMAL



Machine Id **T274** Component

**Diesel Engine** 

PETRO CANADA DURON SHP 10W30 (--- G

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.


### **Fluid Condition**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

GAL)			Jul2023	Mar2024		
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0119952	PCA0100026	
Sample Date		Client Info		06 Mar 2024	26 Jul 2023	
Machine Age	mls	Client Info		216699	191870	
Oil Age	mls	Client Info		216699	0	
Oil Changed		Client Info		Changed	N/A	
Sample Status				NORMAL	NORMAL	
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	
Water		WC Method	>0.2	NEG	NEG	
Glycol		WC Method		NEG	NEG	
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	30	33	
Chromium	ppm	ASTM D5185m	>20	<1	<1	
Nickel	ppm	ASTM D5185m	>4	0	0	
Titanium	ppm	ASTM D5185m		<1	0	
Silver	ppm	ASTM D5185m	>3	0	<1	
Aluminum	ppm	ASTM D5185m	>20	6	3	
Lead	ppm	ASTM D5185m	>40	<1	0	
Copper	ppm	ASTM D5185m	>330	3	2	
Tin	ppm	ASTM D5185m	>15	<1	<1	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	4	3	
Barium	ppm	ASTM D5185m	0	0	0	
Molybdenum	ppm	ASTM D5185m	50	64	65	
Manganese	ppm	ASTM D5185m	0	0	<1	
Magnesium	ppm	ASTM D5185m	950	908	997	
Calcium	ppm	ASTM D5185m	1050	1138	1219	
Phosphorus Zinc	ppm	ASTM D5185m	995 1180	1022	1079	
Sulfur	ppm ppm	ASTM D5185m ASTM D5185m	2600	1253 2747	1351 3216	
CONTAMINAN		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	13	8	
Sodium	ppm	ASTM D5185m	725	<1	2	
Potassium	ppm	ASTM D5185m	>20	9	7	
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.7	0.8	
Nitration	Abs/cm	*ASTM D7624	>20	9.6	10.5	
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.8	23.0	
FLUID DEGRA	NOITAC	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.1	19.7	
Base Number (BN)	mg KOH/g	ASTM D2896		5.9	5.4	




# **OIL ANALYSIS REPORT**





VISUAL		method				history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
<b>Emulsified Water</b>	scalar	*Visual	>0.2	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	


FLUID PROPERTIES		method				history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.7	11.8	

## **GRAPHS**













Certificate L2367

Laboratory Sample No.

: PCA0119952 Lab Number : 06115718 Unique Number : 10924551 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 12 Mar 2024 **Tested** 

: 13 Mar 2024 Diagnosed : 13 Mar 2024 - Wes Davis

NW WHITE & CO - COLUMBIA DIVISION

100 INDEPENDENCE BLVD COLUMBIA, SC US 29210

Contact: GEORGE EDWARDS gedwards@nwwhite.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: