


# **OIL ANALYSIS REPORT**

# (15583Z) Walgreens - Tractor [Walgreens - Tractor] 136A61386

**Diesel Engine** 

PETRO CANADA DURON SHP 10W30 (11 GAL)



## DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the


### **Fluid Condition**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

,				Mar2024		
SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0094046		
Sample Date		Client Info		01 Mar 2024		
Machine Age	mls	Client Info		437999		
Oil Age	mls	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATIO	DN	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0		
Water		WC Method		NEG		
Glycol		WC Method	7 0.2	NEG		
			12		la fina a consel	h'-1 0
WEAR METALS		method	limit/base	current	history1	history2
	ppm	ASTM D5185m	>80	0		
	ppm	ASTM D5185m	>5	0		
	ppm	ASTM D5185m	>2	<1		
	ppm	ASTM D5185m		4		
	ppm	ASTM D5185m	>3	0		
Aluminum	ppm	ASTM D5185m	>30	1		
Lead	ppm	ASTM D5185m	>30	0		
Copper	ppm	ASTM D5185m	>150	10		
Tin	ppm	ASTM D5185m	>5	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	0		
Barium	ppm	ASTM D5185m	0	0		
Molybdenum	ppm	ASTM D5185m	50	57		
Manganese	ppm	ASTM D5185m	0	0		
Magnesium	ppm	ASTM D5185m	950	923		
Calcium	ppm	ASTM D5185m	1050	1112		
Phosphorus	ppm	ASTM D5185m	995	1033		
Zinc	ppm	ASTM D5185m	1180	1242		
Sulfur	ppm	ASTM D5185m	2600	3470		
CONTAMINANT	S	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	5		
Sodium	ppm	ASTM D5185m		<1		
Potassium	ppm	ASTM D5185m	>20	1		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.2		
Nitration	Abs/cm	*ASTM D7624	>20	6.3		
	Abs/.1mm	*ASTM D7415	>30	17.7		
FLUID DEGRADA	MOITA	method	limit/base	current	history1	history2
Oxidation /	Abs/.1mm	*ASTM D7414	>25	14.0		
	mg KOH/g	ASTM D2896		8.3		
= 1.30 · (2.1)				0.0		




# **OIL ANALYSIS REPORT**




VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
<b>Emulsified Water</b>	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		
	DTIEC	ام مالم مما	li.ee:4/le e e e		la i a t a un cel	histow.O


FLUID FROFI	ENTIES	method			HISTOLAL	HISTOLYZ
Visc @ 100°C	cSt	ASTM D445	12.00	11.3		


## **GRAPHS**



# Non-ferrous Metals











Laboratory Sample No. Unique Number: 10925169

Lab Number : 06116336

: PCA0094046

Received **Tested** Diagnosed

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : 12 Mar 2024 : 13 Mar 2024

: 13 Mar 2024 - Wes Davis

Transervice - Shop 1372 - Berkeley-Moreno Valley 17500 Perris Blvd.

Moreno Valley, CA US 92551 Contact: Ryan Cruz

rcruz@transervice.com

Test Package : FLEET Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

T: (951)924-7131 F: (951)924-7151

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)