


OIL ANALYSIS REPORT

(50931Z) Walgreens - Tractor [Walgreens - Tractor] 136A63277

Diesel Engine

PETRO CANADA DURON SHP 10W30 (11 GAL)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

GAL)			Aug2023	Mar2024		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0093932	PCA0093990	
Sample Date		Client Info		01 Mar 2024	18 Aug 2023	
Machine Age	mls	Client Info		111659	55283	
Oil Age	mls	Client Info		55283	0	
Oil Changed		Client Info		Not Changd	Not Changd	
Sample Status				NORMAL	NORMAL	
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	
Water		WC Method	>0.2	NEG	NEG	
Glycol		WC Method		NEG	NEG	
WEAR METAL	_S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>80	17	8	
Chromium	ppm	ASTM D5185m	>5	2	<1	
Nickel	ppm	ASTM D5185m	>2	0	0	
Titanium	ppm	ASTM D5185m		4	<1	
Silver	ppm	ASTM D5185m	>3	<1	0	
Aluminum	ppm	ASTM D5185m	>30	8	<1	
Lead	ppm	ASTM D5185m	>30	0	0	
Copper	ppm	ASTM D5185m	>150	68	88	
Tin	ppm	ASTM D5185m	>5	<1	<1	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	0	14	
Barium	ppm	ASTM D5185m	0	0	0	
Molybdenum	ppm	ASTM D5185m	50	60	58	
Manganese	ppm	ASTM D5185m	0	<1	<1	
Magnesium	ppm	ASTM D5185m	950	951	967	
Calcium	ppm	ASTM D5185m	1050	1158	1183	
Phosphorus	ppm	ASTM D5185m	995	1048	1016	
Zinc	ppm	ASTM D5185m	1180	1275	1223	
Sulfur	ppm	ASTM D5185m	2600	2944	3617	
CONTAMINAN	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	4	3	
Sodium	ppm	ASTM D5185m		1	<1	
Potassium	ppm	ASTM D5185m	>20	20	10	
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.5	0.2	
Nitration	Abs/cm	*ASTM D7624	>20	7.9	5.2	
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.4	17.4	
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.0	12.9	
Base Number (BN)	mg KOH/g	ASTM D2896		7.3	8.7	




OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	


FLUID PROPE	ERITES	method	limit/base		history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.4	11.2	

GRAPHS













Report Id: TSV1372 [WUSCAR] 06116344 (Generated: 03/13/2024 16:38:11) Rev: 1

Laboratory Sample No.

Lab Number : 06116344

Unique Number: 10925177 Test Package : FLEET

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : PCA0093932 Received : 12 Mar 2024 **Tested**

Diagnosed

: 13 Mar 2024 : 13 Mar 2024 - Wes Davis

Transervice - Shop 1372 - Berkeley-Moreno Valley

17500 Perris Blvd. Moreno Valley, CA US 92551 Contact: Ryan Cruz

F: (951)924-7151

rcruz@transervice.com T: (951)924-7131

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)