




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Machine Id
426043
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (9 GAL)



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. (Customer Sample Comment: Resample)

Wear

All component wear rates are normal.

Contamination

Tests indicate that there is no fuel present in the oil. There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0115102	GFL0049341	---
Sample Date	Client Info		07 Mar 2024	28 Jun 2022	---
Machine Age	hrs	Client Info	33520	0	---
Oil Age	hrs	Client Info	600	0	---
Oil Changed	Client Info		Not Chngd	Changed	---
Sample Status			NORMAL	SEVERE	---

CONTAMINATION

	method	limit/base	current	history1	history2
Water	WC Method	>0.2	NEG	NEG	---
Glycol	WC Method		NEG	NEG	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >120	2	21	---
Chromium	ppm	ASTM D5185m >20	0	<1	---
Nickel	ppm	ASTM D5185m >5	<1	<1	---
Titanium	ppm	ASTM D5185m >2	0	<1	---
Silver	ppm	ASTM D5185m >2	0	<1	---
Aluminum	ppm	ASTM D5185m >20	2	1	---
Lead	ppm	ASTM D5185m >40	0	3	---
Copper	ppm	ASTM D5185m >330	0	2	---
Tin	ppm	ASTM D5185m >15	0	<1	---
Vanadium	ppm	ASTM D5185m	0	0	---
Cadmium	ppm	ASTM D5185m	0	0	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	0	19	---
Barium	ppm	ASTM D5185m 0	0	0	---
Molybdenum	ppm	ASTM D5185m 60	59	31	---
Manganese	ppm	ASTM D5185m 0	<1	<1	---
Magnesium	ppm	ASTM D5185m 1010	932	347	---
Calcium	ppm	ASTM D5185m 1070	1010	524	---
Phosphorus	ppm	ASTM D5185m 1150	1022	387	---
Zinc	ppm	ASTM D5185m 1270	1215	466	---
Sulfur	ppm	ASTM D5185m 2060	3334	1362	---

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	3	4	---
Sodium	ppm	ASTM D5185m	5	<1	---
Potassium	ppm	ASTM D5185m >20	0	0	---
Fuel	%	ASTM D3524 >3.0	0.4	▲ 59.5	---

INFRA-RED




	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >4	0.2	---	---
Nitration	Abs/cm	*ASTM D7624 >20	6.5	---	---
Sulfation	Abs/.1mm	*ASTM D7415 >30	18.3	---	---

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	14.5	---	---
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	7.7	---	---







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	14.0	▲ 3.5

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0115102 **Received** : 13 Mar 2024
Lab Number : 06116795 **Tested** : 14 Mar 2024
Unique Number : 10925628 **Diagnosed** : 14 Mar 2024 - Don Baldrige
Test Package : FLEET (Additional Tests: PercentFuel)

GFL Environmental - 405 - Arbor Hills
 7400 Napier Rd
 NORTHVILLE, MI
 US 48168
 Contact: Anthony Hopkins
 ahopkins@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)