

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Component

Transmission (Auto) Fluid

PETRO CANADA DuraDrive HD Synthetic 668

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the fluid.


Fluid Condition

The condition of the fluid is acceptable for the time in service.

68 (QTS)												
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2						
Sample Number		Client Info		GFL0112371	GFL0097942	GFL0097917						
Sample Date		Client Info		08 Mar 2024	15 Nov 2023	12 Oct 2023						
Machine Age	hrs	Client Info		10214	9983	9829						
Oil Age	hrs	Client Info		10662214	431	277						
Oil Changed		Client Info		Changed	Not Changd	Not Changd						
Sample Status				NORMAL	NORMAL	NORMAL						
CONTAMINAT	ION	method	limit/base	current	history1	history2						
Water		WC Method	>0.1	NEG	NEG	NEG						
WEAR METAL	S	method	limit/base	current	history1	history2						
ron	ppm	ASTM D5185m	>160	80	134	72						
Chromium	ppm	ASTM D5185m	>5	0	<1	<1						
Nickel	ppm	ASTM D5185m	>5	0	0	0						
Fitanium	ppm	ASTM D5185m		0	0	0						
Silver	ppm	ASTM D5185m	>5	0	0	0						
Aluminum	ppm	ASTM D5185m	>50	34	42	28						
ead	ppm	ASTM D5185m	>50	0	10	2						
Copper	ppm	ASTM D5185m	>225	12	26	12						
īn	ppm	ASTM D5185m	>10	<1	8	2						
/anadium	ppm	ASTM D5185m		0	<1	0						
Cadmium	ppm	ASTM D5185m		0	0	0						
ADDITIVES		method	limit/base	current	history1	history2						
Boron	ppm	ASTM D5185m		60	53	66						
Barium	ppm	ASTM D5185m		0	0	0						
lolybdenum	ppm	ASTM D5185m		0	<1	<1						
langanese	ppm	ASTM D5185m		<1	2	<1						
lagnesium	ppm	ASTM D5185m		<1	0	2						
Calcium	ppm	ASTM D5185m		121	114	124						
hosphorus	ppm	ASTM D5185m		211	181	208						
linc	ppm	ASTM D5185m		0	0	0						
Sulfur	ppm	ASTM D5185m		1897	1636	1888						
CONTAMINAN	ITS	method	limit/base	current	history1	history2						
Silicon	ppm	ASTM D5185m	>20	9	7	9						
Sodium	ppm	ASTM D5185m		6	6	1						
Potassium	ppm	ASTM D5185m	>20	1	4	3						
VISUAL		method	limit/base	current	history1	history2						
Vhite Metal	scalar	*Visual	NONE	NONE	NONE	NONE						
ellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE						
recipitate	scalar	*Visual	NONE	NONE	NONE	NONE						
Silt	scalar	*Visual	NONE	NONE	NONE	NONE						
Debris	scalar	*Visual	NONE	NONE	NONE	LIGHT						
and/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE						
ppearance	scalar	*Visual	NORML	NORML	NORML	NORML						
Ddor	scalar	*Visual	NORML	NORML	NORML	NORML						
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG						
Free Water	scalar	*Visual		NEG	NEG	NEG						



OIL ANALYSIS REPORT



Color no image no image no image	FLUID PROPE	RTIES	method	limit/base	current	history1	history
Color no image no image no image no image	Visc @ 40°C	cSt	ASTM D445	34	32.0	32.3	32.1
Bottom no image no image no image GRAPHS Ferrous Alloys 0 0 0 0 0 0 0 0 0 0 0 0 0	SAMPLE IMAG	GES	method	limit/base	current	history1	history
	Color				no image	no image	no image
Ferrous Alloys Horning Horni	Bottom				no image	no image	no image
70	Ferrous Alloys	ls		\wedge			



Unique Number : 10926825 Diagnosed : 14 Mar 2024 - Wes Davis Test Package : FLEET Contact: JOSHUA TINKER Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. joshuatinker@gflenv.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Received

Tested

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

: 13 Mar 2024

: 14 Mar 2024

Sample No. : GFL0112371

Lab Number : 06117992

Laboratory

GFL Environmental - 010 - Stockbridge

1280 Rum Creek Parkway

Stockbridge, GA

US 30281

Т:

F: