

OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id **812044**

Component

Transmission (Auto)

PETRO CANADA DuraDrive HD Synthetic 668 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the fluid.


Fluid Condition

The condition of the fluid is acceptable for the time in service.

568 (GAL) ### CONTROL OF THE PROPERTY OF								
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2		
Sample Number		Client Info		GFL0115755	GFL0112297	GFL0107172		
Sample Date		Client Info		11 Mar 2024	16 Feb 2024	05 Feb 2024		
Machine Age	hrs	Client Info		7121	7002	6898		
Oil Age	hrs	Client Info		119	2288	2798		
Oil Changed		Client Info		Not Changd	Changed	Not Changd		
Sample Status				NORMAL	NORMAL	NORMAL		
CONTAMINAT	ΓΙΟΝ	method	limit/base	current	history1	history2		
Water		WC Method	>0.1	NEG	NEG	NEG		
WEAR METAL	_S	method	limit/base	current	history1	history2		
Iron	ppm	ASTM D5185m	>160	85	80	89		
Chromium	ppm	ASTM D5185m	>5	0	<1	<1		
Nickel	ppm	ASTM D5185m	>5	0	<1	0		
Titanium	ppm	ASTM D5185m		0	0	0		
Silver	ppm	ASTM D5185m	>5	0	0	0		
Aluminum	ppm	ASTM D5185m		29	27	28		
Lead	ppm	ASTM D5185m	>50	48	47	50		
Copper	ppm	ASTM D5185m		67	65	74		
Tin	ppm		>10	6	7	6		
Vanadium	ppm	ASTM D5185m	710	0	0	0		
Cadmium	ppm	ASTM D5185m		0	0	0		
ADDITIVES		method	limit/base	current	history1	history2		
Boron	ppm	ASTM D5185m		76	75	82		
Barium	ppm	ASTM D5185m		0	0	5		
Molybdenum	ppm	ASTM D5185m		<1	<1	0		
Manganese	ppm	ASTM D5185m		1	1	<1		
Magnesium	ppm	ASTM D5185m		<1	0	<1		
Calcium	ppm	ASTM D5185m		69	61	70		
Phosphorus	ppm	ASTM D5185m		245	230	237		
Zinc	ppm	ASTM D5185m		0	0	0		
Sulfur	ppm	ASTM D5185m		1224	1028	1112		
CONTAMINA	NTS	method	limit/base	current	history1	history2		
Silicon	ppm	ASTM D5185m	>20	4	4	4		
Sodium	ppm	ASTM D5185m		9	6	<1		
Potassium	ppm	ASTM D5185m	>20	4	2	5		
VISUAL		method	limit/base	current	history1	history2		
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG		
Free Water	scalar	*Visual	2011	NEG	NEG	NEG		
1 100 Walti	Juaiai	Visual		IILG	INLU	INLU		





OIL ANALYSIS REPORT




FLUID PROPE	ERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	34	35.2	35.2	35.3
SAMPLE IMAG	GES	method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image

GRAPHS









Laboratory Sample No.

Lab Number : 06117999 Unique Number : 10926832

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0115755 Received

: 13 Mar 2024 **Tested** : 14 Mar 2024 Diagnosed : 14 Mar 2024 - Wes Davis

GFL Environmental - 010 - Stockbridge 1280 Rum Creek Parkway

Stockbridge, GA US 30281

Contact: JOSHUA TINKER joshuatinker@gflenv.com

Test Package : FLEET To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: