


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
1926737

Component
Rear Differential

Fluid
PETRO CANADA TRAXON SYNTHETIC 75W90 (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	PCA0117935	PCA0112389	PCA0101084
Sample Date	Client Info	04 Feb 2024	13 Nov 2023	29 Aug 2023
Machine Age	mls	391470	371882	353177
Oil Age	mls	391470	371882	353177
Oil Changed	Client Info	Not Changed	Not Changed	Not Changed
Sample Status		NORMAL	NORMAL	NORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Water	WC Method >.2	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >500	192	204	173
Chromium	ppm ASTM D5185m >10	1	2	1
Nickel	ppm ASTM D5185m >10	10	11	10
Titanium	ppm ASTM D5185m	0	<1	0
Silver	ppm ASTM D5185m	0	0	0
Aluminum	ppm ASTM D5185m >25	2	2	2
Lead	ppm ASTM D5185m >25	0	0	0
Copper	ppm ASTM D5185m >100	3	3	2
Tin	ppm ASTM D5185m >10	0	0	0
Vanadium	ppm ASTM D5185m	0	<1	<1
Cadmium	ppm ASTM D5185m	0	<1	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 328	272	334	293
Barium	ppm ASTM D5185m 1	0	0	0
Molybdenum	ppm ASTM D5185m	0	<1	<1
Manganese	ppm ASTM D5185m	5	5	4
Magnesium	ppm ASTM D5185m 1	0	3	0
Calcium	ppm ASTM D5185m 7	0	8	0
Phosphorus	ppm ASTM D5185m 1145	1264	1235	1259
Zinc	ppm ASTM D5185m 3	0	0	0
Sulfur	ppm ASTM D5185m 17909	24854	24704	23304


CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >75	12	16	11
Sodium	ppm ASTM D5185m	2	<1	2
Potassium	ppm ASTM D5185m >20	0	2	0

VISUAL

method	limit/base	current	history1	history2
White Metal	scalar *Visual NONE	NONE	NONE	NONE
Yellow Metal	scalar *Visual NONE	NONE	NONE	NONE
Precipitate	scalar *Visual NONE	NONE	NONE	NONE
Silt	scalar *Visual NONE	NONE	LIGHT	LIGHT
Debris	scalar *Visual NONE	NONE	NONE	NONE
Sand/Dirt	scalar *Visual NONE	NONE	NONE	NONE
Appearance	scalar *Visual NORML	NORML	NORML	NORML
Odor	scalar *Visual NORML	NORML	NORML	NORML
Emulsified Water	scalar *Visual >.2	NEG	NEG	NEG
Free Water	scalar *Visual	NEG	NEG	NEG

OIL ANALYSIS REPORT






FLUID PROPERTIES

method	limit/base	current	history1	history2	
Visc @ 40°C	cSt ASTM D445	99.6	90.6	89.6	90.9

SAMPLE IMAGES

method	limit/base	current	history1	history2	
Color			no image	no image	no image
Bottom			no image	no image	no image

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0117935 **Received** : 14 Mar 2024
Lab Number : **06118656** **Tested** : 15 Mar 2024
Unique Number : 10927489 **Diagnosed** : 15 Mar 2024 - Wes Davis
Test Package : FLEET

PERDUE FARMS - GEORGETOWN
 20621 SAVANAH RD
 GEORGETOWN, DE
 US 19947
 Contact: ROBERT LOCKWOOD
 Robert.Lockwood@Perdue.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: