

# **OIL ANALYSIS REPORT**

## Area (89819X) Walgreens - Tractor Machine Id [Walgreens - Tractor] 136A68031

**Diesel Engine** 

PETRO CANADA DURON SHP 10W30 (11 GAL)

### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.

#### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


tor						
68031						
AL)		May202	3 Sep2023	Feb2024 M	ar2024	
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0110602	PCA0110564	PCA0093475
Sample Date		Client Info		07 Mar 2024	23 Feb 2024	15 Sep 2023
Machine Age	mls	Client Info		215507	214600	203228
Oil Age	mls	Client Info		0	214600	10553
Oil Changed		Client Info		N/A	N/A	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT		method	limit/base	current	history1	history2
Fuel			>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	-
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>80	11	24	22
Chromium	ppm	ASTM D5185m	>5	<1	<1	<1
Nickel	ppm	ASTM D5185m	>2	<1	<1	0
Titanium	ppm	ASTM D5185m	-	11	4	14
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>30	3	4	1
Lead	ppm	ASTM D5185m ASTM D5185m	>30 >150	<1 1	0	0
Copper Tin	ppm ppm		>150	، <1	0	0
Vanadium	ppm	ASTM D5185m	>0	< 1	0	<1
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES	1-1-	method	limit/base	current	history1	history2
Boron	nnm	ASTM D5185m	2	32	16	17
Barium	ppm ppm	ASTM D5185m	_	0	0	0
Molybdenum	ppm	ASTM D5185m	50	49	54	45
Manganese	ppm	ASTM D5185m	0	0	<1	<1
Magnesium	ppm	ASTM D5185m	950	798	746	821
Calcium	ppm	ASTM D5185m	1050	1223	1180	1246
Phosphorus	ppm	ASTM D5185m	995	1030	935	925
Zinc	ppm	ASTM D5185m	1180	1198	1198	1187
Sulfur	ppm	ASTM D5185m	2600	3635	3241	3342
CONTAMINAN	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	4	5	6
Sodium	ppm	ASTM D5185m		2	3	2
Potassium	ppm	ASTM D5185m	>20	1	2	1
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.3	0.6	0.6
Nitration	Abs/cm	*ASTM D7624	>20	7.5	10.7	10.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.7	21.9	21.6
FLUID DEGRA			limit/base		history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.7	18.2	17.0
Base Number (BN)	mg KOH/g	ASTM D2896		7.9	5.7	5.6

Sample Rating Trend

NORMAL



# **OIL ANALYSIS REPORT**



	VISUAL		method				history2
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Mar7/24	Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Ma	Odor	scalar	*Visual	NORML	NORML	NORML	NORML
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
-	Free Water	scalar	*Visual		NEG	NEG	NEG
	FLUID PROPE	ERTIES	method	limit/base	current	history1	history2
-	Visc @ 100°C	cSt	ASTM D445	12.00	11.4	11.5	11.0
	GRAPHS						
	Ferrous Alloys						
10	iron chromium		1				
V Cr L-VV	20 - nickel						
	15-						
	Шdd						
	10						
	5-						
	0		57:				
	May23/23 Sep 15/23		Feb23/24	Mar7/24			
	-		ц.	2			
	Non-ferrous Meta	ls					
	copper						
	8 - tin						
	6-						
	Edd						
	4						
	2	_					
	2-						
			Timmin				
	/lay/23/23 Sep 15/23		-eb23/24	Mar7/24			
	May		Feb	Σ			
	Viscosity @ 100°	C			Base Number	r	
	15 T			8.0			
	14- Abnormal			7.0			
	13			(B/HO	)		
i,	0 12 Base			()(Ho () (Ho () ) ) ) ) ) ) ) ) ) ) ) ) ) ) ) ) ) )	D-		
1000	5 12 5 11 5 11				•		
	10-			<sup></sup> 3.0	•		
	Abnormal			e 2.0	1		
	9 -			1.0	1		
	53		24	0.0		23+-	
	May23/23 Sep 15/23		Feb 23/24	Mar7/24	May23/23	Sep 15/23	670
	Se		ц <u>т</u>	£	W	25 L	
ory :	WearCheck USA - 50	)1 Madisc	n Ave., Cary	, NC 27513	Transer	vice - Shop 1376 -	Berkeley-Lin

Certificate L2367 Test Package : FLEET To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F:

shop1376@transervice.com