

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Area Walgreens - Tractor [Walgreens - Tractor] 136A624120 Component

Diesel Engine

PETRO CANADA DURON SHP 10W30 (11 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

Metal levels are typical for a new component breaking in.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

AL)			Nov2023	Mar2024			
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2	
Sample Number		Client Info		PCA0103660	PCA0103683		
Sample Date		Client Info		05 Mar 2024	29 Nov 2023		
Machine Age	mls	Client Info		51572	30367		
Dil Age	mls	Client Info		21201	30367		
Dil Changed		Client Info		Changed	Changed		
Sample Status				NORMAL	ABNORMAL		
CONTAMINAT		method	limit/base	current	history1	history2	
-uel		WC Method	>2.0	<1.0	<1.0		
Vater		WC Method		NEG	NEG		
Glycol		WC Method	20.L	NEG	NEG		
•	0			-			
WEAR METAL		method	limit/base		history1	history2	
ron	ppm	ASTM D5185m	>100	16	42		
Chromium	ppm	ASTM D5185m		1	1		
Nickel	ppm	ASTM D5185m	>4	<1	0		
Titanium	ppm	ASTM D5185m	0	<1	0		
Silver	ppm	ASTM D5185m		0	<1		
Aluminum	ppm	ASTM D5185m		9	29		
ead	ppm	ASTM D5185m		3	5		
Copper	ppm	ASTM D5185m		3	24		
īn	ppm	ASTM D5185m	>15	2	2		
/anadium	ppm	ASTM D5185m		0	0		
Cadmium	ppm	ASTM D5185m		0	0		
ADDITIVES		method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m	2	10	39		
Barium	ppm	ASTM D5185m	0	0	0		
Nolybdenum	ppm	ASTM D5185m	50	53	59		
Manganese	ppm	ASTM D5185m	0	<1	4		
Magnesium	ppm	ASTM D5185m	950	803	478		
Calcium	ppm	ASTM D5185m	1050	1276	1848		
Phosphorus	ppm	ASTM D5185m	995	1022	1016		
Zinc	ppm	ASTM D5185m	1180	1220	1201		
Sulfur	ppm	ASTM D5185m	2600	3511	2912		
CONTAMINAN	ITS	method	limit/base	current	history1	history2	
Silicon	ppm		>25	10	4 1		
Sodium	ppm	ASTM D5185m		2	3		
Potassium	ppm	ASTM D5185m	>20	19	83		
INFRA-RED		method	limit/base	current	history1	history2	
Soot %	%	*ASTM D7844	>3	0.2	0.3		
Nitration	Abs/cm	*ASTM D7624	>20	7.8	8.7		
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.7	21.8		
FLUID DEGRA	DATION	method	limit/base	current	history1	history2	
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.1	18.9		



OIL ANALYSIS REPORT



Viscosity @ 100°C



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.0	11.6	
GRAPHS						
Ferrous Alloys						
E2/62/09			Mar5/24			
Non-ferrous Meta	ls					
copper						
-						
5						
J-						
)						
Nov29/23			Mar5/24			
Nov			Ň			
Viscosity @ 100°C	2			Base Number		

8.0

7.0

(B/HOX Bw) J

Mar5/24 -

: 18 Mar 2024

: 19 Mar 2024

4.0 -3.0 -3.0 -3.0 -3.0 -1.0 -0.0 -

Vov29/23



 Unique Number
 : 10930216
 Diagnosed
 : 19 Mar 2024 - Wes Davis
 US 18014

 Certificate 12367
 Test Package
 : FLEET
 Contact: Stephen Mackes

 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 smackes@transervice.com

 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 T: (610)837-8103

 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)
 F: (610)837-8105

Received

Tested

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

14

13

8

Lab Number : 06121383

Laboratory Sample No. Vov29/23

: PCA0103660

cSt (100°C)

Contact/Location: Stephen Mackes - TSV1365

Transervice - Shop 1365 - Berkeley-Nazareth

6813 Chrisphalt Drive

Bath Borough, PA

Mar5/24