

## **OIL ANALYSIS REPORT**

#### Area (65637Z) Walgreens - Tractor Machine Id [Walgreens - Tractor] 136A624106

**Diesel Engine** 

PETRO CANADA DURON SHP 10W30 (11 GAL)

### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

Metal levels are typical for a new component breaking in.

#### Contamination

Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.

#### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

AL)			Nov2023	Feb2024		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0103651	PCA0103679	
Sample Date		Client Info		14 Feb 2024	27 Nov 2023	
Aachine Age	mls	Client Info		54752	31426	
Dil Age	mls	Client Info		23008	31426	
Dil Changed		Client Info		Changed	Changed	
Sample Status				NORMAL	NORMAL	
CONTAMINAT	ION	method	limit/base	current	history1	history2
uel		WC Method	>5	<1.0	<1.0	
Vater		WC Method	>0.2	NEG	NEG	
Glycol		WC Method		NEG	NEG	
WEAR METAL	.S	method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>80	29	25	
Chromium	ppm	ASTM D5185m	>5	2	<1	
lickel	ppm	ASTM D5185m	>2	<1	0	
Fitanium	ppm	ASTM D5185m		<1	0	
Silver	ppm	ASTM D5185m	>3	0	0	
Aluminum	ppm	ASTM D5185m	>30	19	2	
ead	ppm	ASTM D5185m	>30	<1	5	
Copper	ppm	ASTM D5185m	>150	277	3	
īn	ppm	ASTM D5185m	>5	2	0	
/anadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	10	241	
Barium	ppm	ASTM D5185m	0	0	0	
Nolybdenum	ppm	ASTM D5185m	50	54	86	
Manganese	ppm	ASTM D5185m	0	1	<1	
<i>I</i> lagnesium	ppm	ASTM D5185m	950	796	416	
Calcium	ppm	ASTM D5185m	1050	1327	1529	
Phosphorus	ppm	ASTM D5185m	995	966	1042	
Zinc	ppm	ASTM D5185m	1180	1168	1293	
Sulfur	ppm	ASTM D5185m	2600	2860	3044	
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	6	4	
Sodium	ppm	ASTM D5185m		2	3	
Potassium	ppm	ASTM D5185m	>20	43	0	
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.5	0.6	
Nitration	Abs/cm	*ASTM D7624	>20	8.6	9.1	
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.6	22.7	
FLUID DEGRAI	DATION	method	limit/base	current	history1	history2
Dxidation	Abs/.1mm	*ASTM D7414	>25	16.4	22.5	
o , il d d l o l l	100,1111		20	10.4	22.0	




Sample Rating Trend




NORMAL



# **OIL ANALYSIS REPORT**





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.3	10.1	
GRAPHS						
Ferrous Alloys						
30 T						
6 1						
iron						
25 - eeeeeeeeeeeeeeeeeeeeeeeeeeeeeeeeeee						
sessesses nickel						
20-						
201						
10						
15						
10						
5-						
			Community of the second se			
			24.			
Nov27/23			Feb14/24			
Vov			- Ge			
_						
Non-ferrous Meta	ls					
<sup>DO</sup> T						
copper			1			
50 - •••••••••••••••••••••••••••••••••••		/				
sssssssss tin						
DO -		/				
	_					
50 -	/					
00-						
50						
0			4			
Nov27/23			Feb14/24			
lov2			eb 1			
			LC			
Viscosity @ 100°C	2			Data Numb		
15 <sub>т</sub>				Base Number		
			9.0	T		
14 - Abnormal			8.0			
1				-		
13						
Base			(0,7.0 (0,40) HOX Just Just Just Just Just Just Just Just	+		
12 Base		******	Ĕ 5.0			
11						
			4.0	1		
10			2 3.0	•		
Abnormal			× 2 0	1		
9-			1.0			

0.0

Vov27/23

Feb14/24 -

: 18 Mar 2024

: 19 Mar 2024



Unique Number : 10930221 Diagnosed : 19 Mar 2024 - Wes Davis US 18014 Test Package : FLEET Contact: Stephen Mackes Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. smackes@transervice.com \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (610)837-8103 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (610)837-8105

Received

Tested

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Vov27/23

: PCA0103651

Laboratory Sample No.

Lab Number : 06121388

Transervice - Shop 1365 - Berkeley-Nazareth

6813 Chrisphalt Drive

Bath Borough, PA

Feb14/24.