

# **OIL ANALYSIS REPORT**

Sample Rating Trend





Component Diesel Engine Fluid

## PETRO CANADA DURON SHP 15W40 (--- GAL)

### DIAGNOSIS Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0114324	GFL0069900	GFL0069874
Sample Date		Client Info		15 Mar 2024	17 May 2023	09 May 2023
Machine Age	hrs	Client Info		16348	0	14869
Oil Age	hrs	Client Info		0	0	600
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>120	9	19	2
Chromium	ppm	ASTM D5185m	>20	<1	1	<1
Nickel	ppm	ASTM D5185m	>5	<1	0	0
Titanium	ppm	ASTM D5185m	>2	<1	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	5	1
Lead	ppm	ASTM D5185m	>40	2	0	0
Copper	ppm	ASTM D5185m	>330	2	<1	0
Tin	ppm	ASTM D5185m	>15	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	2	4	6
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	59	57	59
Manganese	ppm	ASTM D5185m	0	0	<1	<1
Magnesium	ppm	ASTM D5185m	1010	935	935	945
Calcium	ppm	ASTM D5185m	1070	1092	1026	1070
Phosphorus	ppm	ASTM D5185m	1150	1023	1004	1048
Zinc	ppm	ASTM D5185m	1270	1267	1237	1256
Sulfur	ppm	ASTM D5185m	2060	3099	3478	3780
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	4	4	3
Sodium	ppm	ASTM D5185m		4	1	2
Potassium	ppm	ASTM D5185m	>20	3	6	<1
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>4	0.4	0.5	0.1
Nitration	Abs/cm	*ASTM D7624	>20	8.9	8.5	5.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.0	19.6	17.8
FLUID DEGRAD	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.2	15.3	13.8
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	6.9	8.5	7.1



# **OIL ANALYSIS REPORT**

VISUAL



	VISUAL		method	iimit/base		nistory i	nistory2
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
May 17/23 Mari 5/24	Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
May	Odor	scalar	*Visual	NORML	NORML	NORML	NORML
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
	Free Water	scalar	*Visual		NEG	NEG	NEG
	FLUID PROPE	RTIES	method	limit/base	current	history1	history2
	Visc @ 100°C	cSt	ASTM D445	15.4	13.5	13.7	14.2
	GRAPHS						
	Ferrous Alloys						
7/23 -	iron						
May17/23	15 - nickel						
	E 10						
	d IV						
	5						
	May9/23	May17/23		Mar15/24			
		-		W			
	Non-ferrous Metal	S					
	copper						
	8 - tin						
	6 -						
	mdd						
	4						
	2 -			No. of Concession, Name			
	0	and a local division in	And Design and De				
	May9/23	7/23		5/24 -			
	May	May17/23		Mar15/24			
	Viscosity @ 100°C				Base Number		
	<sup>19</sup>			10.0	Base		
	18 - Abnormal			- 8.0			
	17-			(B/HO)			
	016 Base 115 3 14			Ē 6.0			
	513						
	12			ase N			
	12 Abnormal			<sup>66</sup> 2.0			
	11						
	May9/23	May17/23		Mar15/24	May9/23	May17/23	
	Ĩ	May		Mai	W	May	
Laboratory	: WearCheck USA - 50 <sup>-</sup>	1 Madiso	n Ave., Carv	, NC 27513	GFL Env	ironmental -	468 - Dearbo
Laboratory Sample No.	: WearCheck USA - 50 <sup>-</sup> : GFL0114324	Recei	ved : 19	Mar 2024	GFL Env		51 Schaefer F
Sample No. Lab Number	: GFL0114324 : <mark>06122138</mark>	Recei Teste	ved : 19 d : 20	Mar 2024 Mar 2024			468 - Dearbo 51 Schaefer F Dearborn, I
Sample No.	: GFL0114324 : <mark>06122138</mark> : 10936289	Recei	ved : 19 d : 20	Mar 2024			51 Schaefer F



\* - Denotes test metho Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)