


OIL ANALYSIS REPORT

(89951X) Walgreens - Tractor [Walgreens - Tractor] 136A69013

Diesel Engine

PETRO CANADA DURON SHP 10W30 (11 GAL)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

•		Dec	2023	Dec2023 Feb203	24	
SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0117913	PCA0105407	PCA0105403
Sample Date		Client Info		28 Feb 2024	20 Dec 2023	15 Dec 2023
Machine Age	mls	Client Info		544801	526211	524939
Oil Age	mls	Client Info		50000	25000	28300
Oil Changed		Client Info		Changed	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATIO	NC	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METALS	;	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>80	4	15	14
Chromium	ppm	ASTM D5185m	>5	0	2	2
Nickel	ppm	ASTM D5185m	>2	0	<1	<1
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>30	3	12	9
Lead	ppm	ASTM D5185m	>30	0	<1	0
Copper	ppm	ASTM D5185m	>150	1	6	6
Tin	ppm	ASTM D5185m	>5	<1	2	1
Vanadium	ppm	ASTM D5185m		0	0	<1
Cadmium	ppm	ASTM D5185m		0	0	<1
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	3	3	3
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	50	57	63	62
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	950	951	1053	977
Calcium	ppm	ASTM D5185m	1050	1009	1131	1073
Phosphorus	ppm	ASTM D5185m	995	1041	1093	1042
Zinc	ppm	ASTM D5185m	1180	1231	1314	1274
Sulfur	ppm	ASTM D5185m	2600	3521	2926	2794
CONTAMINANT	S	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	6	10	10
Sodium	ppm	ASTM D5185m		<1	1	2
Potassium	ppm	ASTM D5185m	>20	0	3	2
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.2	0.7	0.7
Nitration	Abs/cm	*ASTM D7624	>20	5.1	8.7	8.5
	Abs/.1mm	*ASTM D7415	>30	18.0	21.6	21.4
FLUID DEGRADA	ATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	13.6	18.1	18.0
	mg KOH/g	ASTM D2896		8.9	6.1	6.2
===== (511)	99			0.0	J	U




OIL ANALYSIS REPORT





VISUAL		method				history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPE	RHES	method			history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.7	12.0	11.9

GRAPHS











Certificate L2367

Laboratory Sample No.

Lab Number : 06124253 Unique Number : 10938404

Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : PCA0117913

Received **Tested** Diagnosed

: 20 Mar 2024 : 21 Mar 2024

: 21 Mar 2024 - Wes Davis

Transervice - Shop 1366 - Berkeley-Woodland

2370 East Main Street Woodland, CA US 95776

Contact: Gary Mann gmann@transervice.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (530)666-7771 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (530)406-7971