


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
KENWORTH 158470682

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 10W30 (22 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		PCA0116926	PCA0100897	PCA0094494
Sample Date	Client Info		04 Mar 2024	14 Aug 2023	21 Mar 2023
Machine Age	mls	Client Info	169440	156956	147429
Oil Age	mls	Client Info	0	9527	0
Oil Changed	Client Info		Changed	Changed	N/A
Sample Status			NORMAL	NORMAL	ABNORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<1.0	<1.0	<1.0
Water	WC Method	>0.2	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	0.0

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >75	44	43	33
Chromium	ppm	ASTM D5185m >5	1	1	<1
Nickel	ppm	ASTM D5185m >4	<1	<1	7
Titanium	ppm	ASTM D5185m >2	1	<1	0
Silver	ppm	ASTM D5185m >2	<1	0	0
Aluminum	ppm	ASTM D5185m >15	9	12	4
Lead	ppm	ASTM D5185m >25	<1	<1	<1
Copper	ppm	ASTM D5185m >100	3	2	▲ 397
Tin	ppm	ASTM D5185m >4	<1	<1	3
Vanadium	ppm	ASTM D5185m	<1	0	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 2	5	9	8
Barium	ppm	ASTM D5185m 0	2	0	0
Molybdenum	ppm	ASTM D5185m 50	59	62	58
Manganese	ppm	ASTM D5185m 0	<1	1	2
Magnesium	ppm	ASTM D5185m 950	777	893	105
Calcium	ppm	ASTM D5185m 1050	1163	1144	472
Phosphorus	ppm	ASTM D5185m 995	943	949	1054
Zinc	ppm	ASTM D5185m 1180	1151	1254	1144
Sulfur	ppm	ASTM D5185m 2600	3117	3691	4487

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	6	7	▲ 33
Sodium	ppm	ASTM D5185m	2	3	1
Potassium	ppm	ASTM D5185m >20	19	19	1



INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >6	0.9	0.6	0.4
Nitration	Abs/cm	*ASTM D7624 >20	14.1	12.2	8.1
Sulfation	Abs/.1mm	*ASTM D7415 >30	24.9	20.9	17.2

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	22.3	18.3	14.7
Base Number (BN)	mg KOH/g	ASTM D2896	5.3	6.3	7.4









OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	12.00	10.5	10.3	10.6

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0116926 **Received** : 21 Mar 2024
Lab Number : 06124530 **Tested** : 21 Mar 2024
Unique Number : 10938681 **Diagnosed** : 21 Mar 2024 - Wes Davis
Test Package : MOB 1 (Additional Tests: TBN)

MILLER TRUCK LEASING #114
 63 REPAUPO STATION ROAD
 LOGAN TOWNSHIP, NJ
 US 08085
 Contact: ED DAVIS
 edavis@millertransgroup.com
 T: (856)214-3521
 F: (856)214-3663

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)