

OIL ANALYSIS REPORT

Sample Rating Trend







Machine Id 165485

Component Diesel Engine

PETRO CANADA DURON SHP 10W30 (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0116920		
Sample Date		Client Info		08 Mar 2024		
Machine Age	mls	Client Info		155350		
Oil Age	mls	Client Info		10038		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINATI	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0		
Water		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METALS	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	55		
Chromium	ppm	ASTM D5185m	>20	1		
Nickel	ppm	ASTM D5185m	>20	، <1		
Titanium	ppm	ASTM D5185m	~7	<1		
Silver	ppm	ASTM D5185m	>3	0		
Aluminum	ppm	ASTM D5185m	>20	5		
Lead	ppm	ASTM D5185m	>40	0		
Copper	ppm		>330	2		
Tin	ppm	ASTM D5185m	>15	_ <1		
Vanadium	ppm	ASTM D5185m	210	<1		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES	1-1-	method	limit/base	current	history1	history2
	000	ASTM D5185m	2			
Boron Barium	ppm	ASTM D5185m	2	12 2		
Molybdenum	ppm	ASTM D5185m	50	2 61		
Manganese	ppm ppm	ASTM D5185m	0	<1		
Magnesium		ASTM D5185m	950	<1 822		
Calcium	ppm ppm	ASTM D5185m	1050	1080		
Phosphorus		ASTM D5185m	995	987		
Zinc	ppm ppm	ASTM D5185m	1180	1159		
Sulfur	ppm	ASTM D5185m	2600	3121		
CONTAMINAN		method	limit/base			
				current	history1	history2
Silicon	ppm	ASTM D5185m	>25	5		
Sodium	ppm	ASTM D5185m	. 00	0		
Potassium	ppm	ASTM D5185m	>20	7		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.6		
Nitration	Abs/cm	*ASTM D7624	>20	9.4		
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.0		
FLUID DEGRAD	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.9		
Base Number (BN)	mg KOH/g	ASTM D2896		7.7		





OIL ANALYSIS REPORT



Viscosity @ 100°C







Laboratory

Sample No.

Contact: ED DAVIS edavis@millertransgroup.com T: (856)214-3521 F: (856)214-3663

ñ