


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id **395331**

Component **Diesel Engine**

PETRO CANADA DURON SHP 10W30 (--- 0

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

QTS)		Jul	2023	Nov2023 Jan202	4		
SAMPLE INFORM	ATION	method	limit/base	current	history1	history2	
Sample Number		Client Info		PCA0113585	PCA0105753	PCA0100882	
Sample Date		Client Info		11 Jan 2024	16 Nov 2023	20 Jul 2023	
Machine Age	mls	Client Info		0	159097	139685	
Oil Age	mls	Client Info		0	19495	7643	
Oil Changed		Client Info		Changed	Changed	Changed	
Sample Status				NORMAL	ABNORMAL	ABNORMAL	
CONTAMINATIO	NC	method	limit/base	current	history1	history2	
Fuel		WC Method	>5	<1.0	<1.0	<1.0	
Water		WC Method	>0.2	NEG	NEG	NEG	
Glycol		WC Method		NEG	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185m	>100	12	43	98	
Chromium	ppm	ASTM D5185m	>20	0	1	4	
Nickel	ppm	ASTM D5185m	>4	0	0	<1	
	ppm	ASTM D5185m		0	0	<1	
	ppm	ASTM D5185m	>3	0	0	0	
	ppm	ASTM D5185m	>20	8	<u>^</u> 22	<u></u> 54	
	ppm	ASTM D5185m	>40	0	0	0	
	ppm		>330	0	0	6	
	ppm	ASTM D5185m	>15	0	0	2	
	ppm	ASTM D5185m		0	0	<1	
	ppm	ASTM D5185m		0	0	<1	
ADDITIVES		method	limit/base	current	history1	history2	
	ppm		2	5	0	6	
	ppm	ASTM D5185m		0	4	<1	
	ppm	ASTM D5185m	50	67	66	74	
	ppm	ASTM D5185m		0	0	2	
	ppm	ASTM D5185m	950	1092	918	1022	
	ppm	ASTM D5185m	1050	1316	1282	1280	
	ppm	ASTM D5185m	995 1180	1204	1059 1285	1069 1348	
	ppm ppm	ASTM D5185m ASTM D5185m	2600	1484 4197	3532	3576	
CONTAMINANT		method	limit/base	current	history1	history2	
			>25	3	0	8	
	ppm ppm	ASTM D5185m	>23	ა <1	0	5	
	ppm	ASTM D5185m	>20	5	22	<u>↓</u> 42	
INFRA-RED		method	limit/base	current	history1	history2	
	%	*ASTM D7844	>3	0.3	0.7	1.2	
	Abs/cm	*ASTM D7624	>20	8.8	13.2	16.3	
	Abs/.1mm	*ASTM D7415		18.6	23.1	28.5	
FLUID DEGRADATION method limit/base current history1 history2							
	Abs/.1mm	*ASTM D7414	>25	15.8	21.6	26.7	
	mg KOH/g	ASTM D7414 ASTM D2896	725	8.6	6.6	6.3	
_ 000				0.0	0.0	0.0	



OIL ANALYSIS REPORT



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	RTIES	method	limit/base	current	history1	history2

Visc @ 100°C	cSt	ASTM D445	12.00	11.3	11.6	12.3
GRAPHS						
Iron (ppm)				Lead (ppm)		
250 Severe				80 Severe		
150				= 60		
Abnormal				Abnormal		
50	_			20		
- S3 + 0	73		24	0 23		724
Jul20/23	Nov16/23		Jan11/24	Jul20/23	Nov16/23	Jan11/24
Aluminum (ppm)				Chromium	(ppm)	
50				Severe		1
40 Severe						
Abnormal				Abnormal		
10			_	10		
0 1 23	73		724	- L33	123	/24
Jul20/23	Nov16/23		Jan11/24	Jul20/23	Nov16/23	Jan11/24
Copper (ppm)				Silicon (ppn	n)	
400 T Severe				80 Severe		
300				60		
E 200				Abnormal		
100				20		
1/23	,73		724	1/23	/23	724
Jul20/23	Nov16/23		Jan11/24	Jul20/23	Nov16/23	Jan11/24
Viscosity @ 100°C				Base Numb	er	
16 Abnormal				0.0 J		
14 Abnormal	nnnneee		-	g 6.0		
000112 Base				4.0 4.0		
Abnormal				8.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0		
8 1 EZ/0	3/23		1/24	0.0	3/23 -	
Jul20/23	Nov16/23		Jan11/24	Jul20/23	Nov16/23	Jan11/24





Laboratory Sample No.

Lab Number : 06124672 **Unique Number** : 10938823

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : PCA0113585

Received **Tested** Diagnosed

: 21 Mar 2024 : 22 Mar 2024

: 22 Mar 2024 - Wes Davis

63 REPAUPO STATION ROAD LOGAN TOWNSHIP, NJ US 08085

Contact/Location: ED DAVIS - MILLOG

MILLER TRUCK LEASING #114

Contact: ED DAVIS edavis@millertransgroup.com

T: (856)214-3521 F: (856)214-3663

Test Package: MOB 1 (Additional Tests: TBN) To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: MILLOG [WUSCAR] 06124672 (Generated: 03/22/2024 04:38:48) Rev: 1

Page 2 of 2