

OIL ANALYSIS REPORT

Sample





Component **Diesel Engine**

PETRO CANADA DURON SHP 15W40 (16 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

GAL)		3v2016 Oct2	017 Apr2018 Jan2019	Mar2022 May2023 Jul2023	0et2023	
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0111546	GFL0083139	GFL0083143
Sample Date	la u a	Client Info		12 Feb 2024	30 Oct 2023	25 Sep 2023
Machine Age	hrs	Client Info		0	0	0
Oil Changed	hrs	Client Info		0 N/A	0 N/A	N/A
Oil Changed		Client Info		N/A NORMAL	NORMAL	N/A NORMAL
Sample Status					_	
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	0.3
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	_S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	52	16	29
Chromium	ppm	ASTM D5185m	>20	4	<1	1
Nickel	ppm	ASTM D5185m	>4	<1	0	0
Titanium	ppm	ASTM D5185m		<1	0	<1
Silver	ppm	ASTM D5185m	>3	<1	0	0
Aluminum	ppm	ASTM D5185m	>20	5	3	5
Lead	ppm	ASTM D5185m	>40	4	<1	<1
Copper	ppm	ASTM D5185m	>330	68	1	15
Tin	ppm	ASTM D5185m	>15	2	0	2
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	<1	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	15	1	1
Barium	ppm	ASTM D5185m	0	2	0	0
Molybdenum	ppm	ASTM D5185m	60	68	65	70
Manganese	ppm	ASTM D5185m	0	2	0	2
Magnesium	ppm	ASTM D5185m	1010	823	940	959
Calcium	ppm	ASTM D5185m	1070	1404	1068	1295
Phosphorus	ppm	ASTM D5185m	1150	886	1018	1072
Zinc	ppm	ASTM D5185m	1270	1148	1238	1359
Sulfur	ppm	ASTM D5185m	2060	2437	3535	2515
CONTAMINAN	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	17	7	8
Sodium	ppm	ASTM D5185m		2	0	5
Potassium	ppm	ASTM D5185m	>20	3	2	8
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	1.3	1.2	0.4
Nitration	Abs/cm	*ASTM D7624	>20	12.3	8.8	8.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	24.6	20.8	19.7
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	22.0	16.1	15.8
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	5.2	9.8	8.3
(211)				U.		



OIL ANALYSIS REPORT








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPERTIES		method				history2
Visc @ 100°C	cSt	ASTM D445	15.4	13.9	14.2	12.3

GRAPHS













Certificate L2367

Laboratory Sample No.

Lab Number : 06124772 Unique Number: 10938923 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0111546 Received **Tested**

Diagnosed

: 21 Mar 2024 : 22 Mar 2024

: 22 Mar 2024 - Wes Davis

GFL Environmental - 074 - Douglas - Transwaste

1219 Landfill Road Douglas, GA US 31533

Contact: CURTIS JACOBS

CURTIS.JACOBS@GFLENV.COM T: (912)384-6001

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)