


OIL ANALYSIS REPORT

(TEMP) Preferred Service-Tractor [Preferred Service-Tractor] 192A32036B

Diesel Engine

PETRO CANADA DURON UHP 5W30 (36 QTS)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Metal levels are typical for a new component breaking in.

Contamination

There is no indication of any contamination in the


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

) (S)			Dec2023	Mar2024		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0116684	PCA0114386	
Sample Date		Client Info		12 Mar 2024	06 Dec 2023	
Machine Age	mls	Client Info		54382	27894	
Oil Age	mls	Client Info		26508	25894	
Oil Changed		Client Info		Oil Added	Not Changd	
Sample Status				NORMAL	NORMAL	
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>6.0	<1.0	<1.0	
Water		WC Method	>0.2	NEG	NEG	
Glycol		WC Method		NEG	NEG	
WEAR METAL	.S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	29	38	
Chromium	ppm	ASTM D5185m	>20	<1	<1	
Nickel	ppm	ASTM D5185m	>2	2	2	
Titanium	ppm	ASTM D5185m		<1	<1	
Silver	ppm	ASTM D5185m	>2	0	<1	
Aluminum	ppm	ASTM D5185m	>25	14	30	
Lead	ppm	ASTM D5185m	>40	<1	<1	
Copper	ppm	ASTM D5185m	>330	247	321	
Tin	ppm	ASTM D5185m	>15	2	5	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	<1	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	32	230	
Barium	ppm	ASTM D5185m	0	0	13	
Molybdenum	ppm	ASTM D5185m	64	72	128	
Manganese	ppm	ASTM D5185m	0	1	5	
Magnesium	ppm	ASTM D5185m	1160	1068	668	
Calcium	ppm	ASTM D5185m	820	968	1489	
Phosphorus	ppm	ASTM D5185m	1160	1034	691	
Zinc	ppm	ASTM D5185m	1260	1297	890	
Sulfur	ppm	ASTM D5185m	3000	3001	2438	
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	18	71	
Sodium	ppm	ASTM D5185m		4	4	
Potassium	ppm	ASTM D5185m	>20	38	72	
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.6	0.5	
Nitration	Abs/cm	*ASTM D7624	>20	10.1	10.1	
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.6	24.9	
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	20.3	23.0	
Base Number (BN)	mg KOH/g	ASTM D2896	11.0	7.1	7.4	




OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	


FLUID PROP	ERHES	method	limit/base		history1	history2
Visc @ 100°C	cSt	ASTM D445	11.9	11.2	9.7	

GRAPHS













Laboratory Sample No.

Lab Number : 06126122

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : PCA0116684

Unique Number : 10940273 Test Package : FLEET

Received : 22 Mar 2024 **Tested** : 22 Mar 2024

Diagnosed : 22 Mar 2024 - Wes Davis

Transervice - Shop 1920 - Preferred Service

1955 W. North Avenue, Bldg K Melrose Park, IL

US 60160 Contact: Tom Lindeman tlindemann@transervice.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (630)376-8946