


OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Machine Id
Volvo 1926706

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 10W30 (42 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		PCA0118712	PCA0113691	PCA0105969
Sample Date	Client Info		14 Mar 2024	20 Dec 2023	02 Oct 2023
Machine Age	mls	Client Info	482780	465779	447009
Oil Age	mls	Client Info	17001	38617	19847
Oil Changed	Client Info		Not Changed	Changed	Not Changed
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>6.0	<1.0	<1.0	<1.0
Water	WC Method	>0.2	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >100	39	35	24
Chromium	ppm	ASTM D5185m >20	1	<1	<1
Nickel	ppm	ASTM D5185m >2	1	<1	<1
Titanium	ppm	ASTM D5185m	<1	<1	<1
Silver	ppm	ASTM D5185m >2	<1	0	0
Aluminum	ppm	ASTM D5185m >25	3	2	2
Lead	ppm	ASTM D5185m >40	2	1	2
Copper	ppm	ASTM D5185m >330	9	8	6
Tin	ppm	ASTM D5185m >15	1	<1	<1
Vanadium	ppm	ASTM D5185m	<1	0	0
Cadmium	ppm	ASTM D5185m	<1	0	<1

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 2	2	0	0
Barium	ppm	ASTM D5185m 0	2	10	0
Molybdenum	ppm	ASTM D5185m 50	60	59	61
Manganese	ppm	ASTM D5185m 0	2	<1	1
Magnesium	ppm	ASTM D5185m 950	942	879	1121
Calcium	ppm	ASTM D5185m 1050	1096	1008	1240
Phosphorus	ppm	ASTM D5185m 995	1007	1001	1088
Zinc	ppm	ASTM D5185m 1180	1233	1140	1445
Sulfur	ppm	ASTM D5185m 2600	3132	2943	3500

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	6	4	4
Sodium	ppm	ASTM D5185m	4	10	8
Potassium	ppm	ASTM D5185m >20	4	4	3



INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	0.4	0.6	0.5
Nitration	Abs/cm	*ASTM D7624 >20	8.2	9.7	8.6
Sulfation	Abs/.1mm	*ASTM D7415 >30	19.2	22.6	19.8

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	15.9	19.0	16.2
Base Number (BN)	mg KOH/g	ASTM D2896	7.7	5.7	6.8





OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	12.00	11.1	11.0	11.2

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0118712 **Received** : 25 Mar 2024
Lab Number : **06127516** **Tested** : 26 Mar 2024
Unique Number : 10941667 **Diagnosed** : 26 Mar 2024 - Wes Davis
Test Package : FLEET

PERDUE FARMS - ACCOMAC
 22520 LANKFORD HWY
 ACCOMAC, VA
 US 23301
 Contact: PEGGY KIMES
 peggy.kimes@perdue.com
 T: (757)787-5304
 F: (757)787-5208

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)