

OIL ANALYSIS REPORT

Sample Rating Trend


NORMAL



Machine Id
728096
Component
Diesel Engir

Diesel Engine

PETRO CANADA DURON SHP 15W40 (--- GAL)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

	GAL)			Mar2024		
SAMPLE INFOR	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0111931		
Sample Date		Client Info		08 Mar 2024		
Machine Age	hrs	Client Info		20458		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINA	TION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0		
Water		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METAI	LS	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>80	64		
Chromium	ppm	ASTM D5185m	>5	<1		
Nickel	ppm	ASTM D5185m	>2	<1		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m	>3	0		
Aluminum	ppm	ASTM D5185m	>30	7		
Lead	ppm	ASTM D5185m	>30	<1		
Copper	ppm	ASTM D5185m	>150	2		
Tin	ppm	ASTM D5185m	>5	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	10		
Barium	ppm	ASTM D5185m	0	0		
Molybdenum	ppm	ASTM D5185m	60	48		
Manganese	ppm	ASTM D5185m	0	<1		
Magnesium	ppm	ASTM D5185m	1010	870		
Calcium	ppm	ASTM D5185m	1070	1187		
Phosphorus	ppm	ASTM D5185m	1150	957		
Zinc	ppm	ASTM D5185m	1270	1102		
Sulfur	ppm	ASTM D5185m	2060	3325		
CONTAMINA	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	5		
Sodium	ppm	ASTM D5185m		10		
Potassium	ppm	ASTM D5185m	>20	2		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	2.6		
Nitration	Abs/cm	*ASTM D7624	>20	11.5		
Sulfation	Abs/.1mm	*ASTM D7415	>30	23.5		
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.3		
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	7.5		




OIL ANALYSIS REPORT




VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		


FLUID PROPI	ERITES	method			riistory i	History
Visc @ 100°C	cSt	ASTM D445	15.4	12.5		

GRAPHS



10-	Non-ferrous Metals
8-	copper copper copper tin
6-	
4-	
2 -	
0.	Mar8/2-4







Laboratory Sample No.

Test Package : FLEET

: GFL0111931 Lab Number : 06127599 Unique Number : 10941750

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received **Tested** Diagnosed

: 25 Mar 2024 : 26 Mar 2024 : 26 Mar 2024 - Wes Davis

GFL Environmental - 959F - Clinton HC

9550 Heritage Rd Clinton, IL US 61727

Contact: Larry Siegmann lsiegmann@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: