

OIL ANALYSIS REPORT

Sample Rating Trend





Machine Id DT823 Component

Rear Differential

PETRO CANADA TRAXON SYNTHETIC 75W90 (3 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0113150	PCA0091205	
Sample Date		Client Info		13 Mar 2024	13 Feb 2023	
Machine Age	mls	Client Info		75265	24693	
Oil Age	mls	Client Info		75265	24693	
Oil Changed		Client Info		Changed	Not Changd	
Sample Status				NORMAL	ABNORMAL	
CONTAMINAT	ION	method	limit/base	current	history1	history2
Water		WC Method	>.2	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>1200	200	149	
Chromium	ppm	ASTM D5185m	>8	1	1	
Nickel	ppm	ASTM D5185m	>20	9	7	
Titanium	ppm	ASTM D5185m	>4	<1	0	
Silver	ppm	ASTM D5185m		0	0	
Aluminum	ppm	ASTM D5185m	>30	3	2	
Lead	ppm	ASTM D5185m	>25	0	0	
Copper	ppm	ASTM D5185m	>50	1	1	
Tin	ppm	ASTM D5185m	>5	<1	<1	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	328	151	172	
Barium	ppm	ASTM D5185m	1	0	<1	
Molybdenum	ppm	ASTM D5185m		0	1	
Manganese	ppm	ASTM D5185m		3	3	
Magnesium	ppm	ASTM D5185m	1	10	7	
Calcium	ppm	ASTM D5185m	7	43	44	
Phosphorus	ppm	ASTM D5185m	1145	1129	988	
Zinc	ppm	ASTM D5185m	3	18	22	
Sulfur	ppm	ASTM D5185m	17909	29195	26163	
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>230	134	114	
Sodium	ppm	ASTM D5185m		3	4	
Potassium	ppm	ASTM D5185m	>20	3	1	
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	🔺 MODER	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>.2	NEG	NEG	



OIL ANALYSIS REPORT



	FLUID PROPE	ERTIES m	ethod	limit/base	current	history1	history2
	Visc @ 40°C	cSt AST	TM D445	99.6	94.6	95.7	
	SAMPLE IMA	GES m	lethod	limit/base	current	history1	history2
24	Color				no image	no image	no image
Mar13/	Bottom				no image	no image	no image
	GRAPHS			-			
	Ferrous Alloys	lls		/24 Mar13/24 Mar13/24 Mar13/24			
	Viscosity @ 40°C			Marl			
	중 110 						
				Mar13/24			
Laboratory Sample No. Lab Number Unique Number Test Package	: WearCheck USA - 50 : PCA0113150 : 06129674 : 10943825 : FLEET	01 Madison Av Received Tested Diagnose	ve., Cary, : 26 : 27 d : 27	NC 27513 Mar 2024 Mar 2024 Mar 2024 - W	NW WH	ITE & CO - ANDE 2 P Contact:	RSON DIVISION 605 RIVER RD IEDMONT, SC US 29673 James Threatt



* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F:

jthreatt@nwwhite.com

T: (864)918-4646