

OIL ANALYSIS REPORT



NORMAL



Machine Id **474076** Component

Diesel Engine

PETRO CANADA DURON SHP 15W40 (--- G

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

						· •
AL)				Mar2024		
SAMPLE INFOR	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0089561		
Sample Date		Client Info		26 Mar 2024		
Machine Age	hrs	Client Info		0		
Dil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINA	TION	method	limit/base	current	history1	history2
uel		WC Method	>5	<1.0		
Vater		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METAI	I S	method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>100	59 2		
Chromium	ppm	ASTM D5185m	>20	3		
lickel	ppm	ASTM D5185m	>4	<1 2		
itanium	ppm	ASTM D5185m	0			
Silver	ppm	ASTM D5185m	>3	0		
lluminum	ppm	ASTM D5185m	>20	3		
ead	ppm	ASTM D5185m	>40	12		
Copper	ppm	ASTM D5185m	>330	65		
in 	ppm	ASTM D5185m	>15	2		
anadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	4		
Barium	ppm	ASTM D5185m	0	<1		
Nolybdenum	ppm	ASTM D5185m	60	68		
Manganese	ppm	ASTM D5185m	0	1		
/lagnesium	ppm	ASTM D5185m	1010	934		
Calcium	ppm	ASTM D5185m	1070	1135		
Phosphorus	ppm	ASTM D5185m	1150	1106		
Zinc	ppm	ASTM D5185m	1270	1243		
Gulfur	ppm	ASTM D5185m	2060	2404		
CONTAMINA	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	13		
Sodium	ppm	ASTM D5185m		6		
Potassium	ppm	ASTM D5185m	>20	3		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	2		
litration	Abs/cm	*ASTM D7624	>20	15.5		
Sulfation	Abs/.1mm	*ASTM D7415	>30	26.7		
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	24.8		
Base Number (BN)		ASTM D2896	9.8	6.7		
Jaco Hamber (DIV)	mg Non/g	, IOTHI DE000	0.0	0.7		




OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		
FLUID PROPE	RTIFS	method	limit/base	current	historv1	historv2

FLUID PROPE	ERITES	method	ilmit/base	current	nistory i	nistory2
Visc @ 100°C	cSt	ASTM D445	15.4	14.2		



⁰ T==	сорре			_	_	_	_	_	_	_	
	manana lead										
0 -	menere [III]	J									
10											
10											
20											
0-			 ******	 							
0			 	 							
Mar26/24											









Laboratory Sample No.

: GFL0089561 Lab Number : 06130117

Unique Number : 10949582

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 27 Mar 2024 **Tested**

: 27 Mar 2024 Diagnosed : 27 Mar 2024 - Wes Davis

GFL Environmental - 732 - Thomaston Hauling 2616 Waynmansville Road

Thomaston, GA US 30286 Contact: Michael Taft

Test Package : FLEET

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: