


# OIL ANALYSIS REPORT

Sample Rating Trend



**NORMAL**



Area  
**(89619X) Walgreens - Tractor**  
 Machine Id  
**[Walgreens - Tractor] 136A68007**  
 Component  
**Diesel Engine**  
 Fluid  
**PETRO CANADA DURON SHP 10W30 (11 GAL)**

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	<b>PCA0110516</b>	PCA0093464	PCA0096556
Sample Date	Client Info	<b>15 Mar 2024</b>	17 Oct 2023	24 Apr 2023
Machine Age	mls Client Info	<b>225465</b>	217445	388228
Oil Age	mls Client Info	<b>0</b>	0	388228
Oil Changed	Client Info	<b>N/A</b>	Changed	Changed
Sample Status		<b>NORMAL</b>	NORMAL	NORMAL

## CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >5	<b>&lt;1.0</b>	<1.0	<1.0
Water	WC Method >0.2	<b>NEG</b>	NEG	NEG
Glycol	WC Method	<b>NEG</b>	NEG	NEG

## WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >80	<b>29</b>	47	18
Chromium	ppm ASTM D5185m >5	<b>1</b>	2	<1
Nickel	ppm ASTM D5185m >2	<b>&lt;1</b>	<1	0
Titanium	ppm ASTM D5185m	<b>4</b>	21	6
Silver	ppm ASTM D5185m >3	<b>0</b>	0	0
Aluminum	ppm ASTM D5185m >30	<b>3</b>	3	<1
Lead	ppm ASTM D5185m >30	<b>&lt;1</b>	<1	0
Copper	ppm ASTM D5185m >150	<b>1</b>	2	<1
Tin	ppm ASTM D5185m >5	<b>2</b>	0	<1
Vanadium	ppm ASTM D5185m	<b>&lt;1</b>	0	0
Cadmium	ppm ASTM D5185m	<b>&lt;1</b>	<1	0

## ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 2	<b>9</b>	11	15
Barium	ppm ASTM D5185m 0	<b>0</b>	3	0
Molybdenum	ppm ASTM D5185m 50	<b>53</b>	43	48
Manganese	ppm ASTM D5185m 0	<b>&lt;1</b>	<1	<1
Magnesium	ppm ASTM D5185m 950	<b>834</b>	685	778
Calcium	ppm ASTM D5185m 1050	<b>1089</b>	1233	1336
Phosphorus	ppm ASTM D5185m 995	<b>880</b>	949	962
Zinc	ppm ASTM D5185m 1180	<b>1115</b>	1099	1216
Sulfur	ppm ASTM D5185m 2600	<b>3380</b>	3097	3612

## CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >20	<b>7</b>	9	7
Sodium	ppm ASTM D5185m	<b>5</b>	15	7
Potassium	ppm ASTM D5185m >20	<b>3</b>	8	5



## INFRA-RED

method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >3	<b>1</b>	1.4	0.5
Nitration	Abs/cm *ASTM D7624 >20	<b>13.5</b>	15.0	9.8
Sulfation	Abs/.1mm *ASTM D7415 >30	<b>23.6</b>	29.0	19.2

## FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	<b>21.3</b>	26.3	14.7
Base Number (BN)	mg KOH/g ASTM D2896	<b>6.1</b>	5.0	7.8





# OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.2	11.8

## GRAPHS



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : PCA0110516  
**Lab Number** : 06131333  
**Unique Number** : 10950798  
**Test Package** : FLEET

**Received** : 27 Mar 2024  
**Tested** : 28 Mar 2024  
**Diagnosed** : 28 Mar 2024 - Wes Davis

**Transervice - Shop 1376 - Berkeley-Linden**  
 3425 Tremley Point Road  
 Linden, NJ  
 US 07036

Contact: Shop 1376 Oil Analysis  
 shop1376@transervice.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
F: