


OIL ANALYSIS REPORT

(50940Z) Walgreens - Tractor [Walgreens - Tractor] 136A63259

Diesel Engine

PETRO CANADA DURON SHP 10W30 (11 GAL)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

			Sep.2023	Mar2024		
SAMPLE INFORMA	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0110515	PCA0105686	
Sample Date		Client Info		15 Mar 2024	22 Sep 2023	
	nls	Client Info		126292	70410	
Oil Age	mls	Client Info		55882	50000	
Oil Changed		Client Info		Changed	Changed	
Sample Status				NORMAL	NORMAL	
CONTAMINATIC	N	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	
Water		WC Method	>0.2	NEG	NEG	
Glycol		WC Method		NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron p	opm	ASTM D5185m	>80	52	46	
	opm	ASTM D5185m	>5	5	3	
	opm	ASTM D5185m	>2	<1	<1	
	opm	ASTM D5185m		<1	<1	
	opm	ASTM D5185m	>3	0	<1	
	opm	ASTM D5185m	>30	14	26	
	opm	ASTM D5185m	>30	<1	0	
_	opm	ASTM D5185m		70	133	
	opm		>5	2	2	
	opm	ASTM D5185m		- <1	0	
	opm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron r	opm	ASTM D5185m	2	3	9	
	opm	ASTM D5185m	0	0	0	
	opm	ASTM D5185m	50	61	54	
	opm		0	1	2	
	opm	ASTM D5185m	950	982	869	
,	opm		1050	1170	1165	
	opm	ASTM D5185m	995	914	881	
	opm	ASTM D5185m	1180	1206	1129	
	opm	ASTM D5185m	2600	2477	2107	
CONTAMINANT	S	method	limit/base	current	history1	history2
	opm	ASTM D5185m	>20	7	6	
	opm	ASTM D5185m		4	2	
	opm	ASTM D5185m	>20	32	66	
INFRA-RED		method	limit/base	current	history1	history2
	%	*ASTM D7844	>3	1.1	0.7	
	Abs/cm	*ASTM D7624	>20	10.4	9.2	
	Abs/.1mm	*ASTM D7024	>30	22.0	20.8	
FLUID DEGRADA		method	limit/base	current	history1	history2
	Abs/.1mm	*ASTM D7414 ASTM D2896	>25	19.9	17.7	
Dast Nulliber (DIV)	ng KOH/g	49 LINI D5030		6.0	6.9	




OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	


FLUID PROPE	ERTIES	method				history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.2	11.0	

GRAPHS











Certificate L2367

Laboratory Sample No.

Test Package : FLEET

: PCA0110515 Lab Number : 06131334 Unique Number: 10950799

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received **Tested**

Diagnosed

: 27 Mar 2024

: 28 Mar 2024 : 28 Mar 2024 - Wes Davis

Transervice - Shop 1374 - Berkeley-Hartford

80 International Drive Windsor, CT US 06095

F: (860)687-1476

Contact: Paul Santanella psantanella@transervice.com

T: (860)687-1037

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)