

OIL ANALYSIS REPORT

Sample Rating Trend




MONTGOMERY **MACK 420043**



Component **Diesel Engine**

PETRO CANADA DURON SHP 15W40 (--- LTR)






DIAGNOSIS	SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Recommendation	Sample Number		Client Info		GFL0115600	GFL0088639	GFL0087963
Resample at the next service interval to monitor.	Sample Date		Client Info		27 Mar 2024	19 Feb 2024	28 Dec 2023
Vear	Machine Age	hrs	Client Info		9157	1529	12209
Il component wear rates are normal.	Oil Age	hrs	Client Info		9157	1529	2107
Contamination	Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
here is no indication of any contamination in the	Sample Status				NORMAL	NORMAL	NORMAL
il. Iuid Condition	CONTAMINAT	ION	method	limit/base	current	history1	history2
Fluid Condition The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
	Water		WC Method	>0.2	NEG	NEG	NEG
	Glycol		WC Method		NEG	NEG	NEG
	WEAR METAL	S	method	limit/base	current	history1	history2
	Iron	ppm	ASTM D5185m	>120	3	5	2
	Chromium	ppm	ASTM D5185m	>20	0	<1	<1
	Nickel	ppm	ASTM D5185m	>5	0	<1	0
	Titanium	ppm	ASTM D5185m		0	0	<1
	Silver	ppm	ASTM D5185m		0	0	0
	Aluminum	ppm	ASTM D5185m		<1	1	<1
	Lead	ppm	ASTM D5185m		0	0	0
	Copper	ppm	ASTM D5185m		<1	9	<1
	Tin	ppm	ASTM D5185m		0	<1	<1
	Vanadium	ppm	ASTM D5185m	210	0	0	0
	Cadmium	ppm	ASTM D5185m		0	0	0
	ADDITIVES		method	limit/base	current	history1	history2
	Boron	ppm	ASTM D5185m	0	2	3	5
	Barium	ppm	ASTM D5185m		0	3	0
	Molybdenum	ppm	ASTM D5185m		59	54	60
	Manganese	ppm	ASTM D5185m		0	0	<1
	Magnesium	ppm	ASTM D5185m		1053	818	969
	Calcium		ASTM D5185m		1135	968	1113
	Phosphorus	ppm	ASTM D5185m		1101	960	1010
	Zinc	ppm	ASTM D5185m ASTM D5185m			1065	1297
	Sulfur	ppm ppm	ASTM D5185m		1333 3852	3076	3243
				limit/base			history2
	CONTAMINAN					history1	
	Silicon	ppm	ASTM D5185m	>20	2	5	5
	Sodium	ppm	ASTM D5185m	. 00	1	0	3
	Potassium	ppm	ASTM D5185m		0	2	2
			method	limit/base		history1	history2
	INFRA-RED						
	INFRA-RED Soot %	%	*ASTM D7844	>4	0.1	0.3	0.2
		% Abs/cm	*ASTM D7844 *ASTM D7624		0.1 5.7	0.3 7.5	0.2 5.9
	Soot %			>20			
	Soot % Nitration	Abs/cm Abs/.1mm	*ASTM D7624 *ASTM D7415	>20	5.7 17.7	7.5	5.9
	Soot % Nitration Sulfation	Abs/cm Abs/.1mm	*ASTM D7624 *ASTM D7415 method	>20 >30 limit/base	5.7 17.7	7.5 18.7	5.9 18.0




12

Mar15/22

OIL ANALYSIS REPORT



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	14.1	13.8	14.0
GRAPHS						
Ferrous Alloys						



* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

25

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)