

OIL ANALYSIS REPORT

SAMPLE IN

Sample Rating Trend

NORMAL

GRIND ROOM [98827289]

KR-GR-003073 - DUMPER 7A - SOUTH (S/N GRIND A -

Hydraulic System

AW HYDRAULIC OIL ISO 68 (10 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. (Customer Sample Comment: 98827289)

All component wear rates are normal.

Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


| FORMATION | method | | | | | |
|-----------|---------|----------------|------------|----------------|------------|------|
| | 12020 N | ar2021 Sep2021 | Jan2022 Ju | un2022 Nov2022 | May2023 Oc | 2023 |
| | | | | | | |
| | | | | | | |
| 11513014) | | | | | | |
| 44540044\ | | | | | | |
| | | | | | | |
| | | | | | | |
| | | | | | | |
| | | | | | | 1 |
| . • | | | | | | |


| Sample Number Sample Date | | Client Info | | PCA0115888 13 Mar 2024 | PCA0106508 20 Dec 2023 | PCA0110823 29 Nov 2023 |
|---------------------------|----------|--------------|------------|---------------------------|---------------------------|---------------------------|
| Machine Age | hrs | Client Info | | 0 | 0 | 0 |
| Oil Age | hrs | Client Info | | 0 | 0 | 0 |
| Oil Changed | | Client Info | | N/A | Not Changd | N/A |
| Sample Status | | | | NORMAL | NORMAL | NORMAL |
| CONTAMINAT | ION | method | limit/base | current | history1 | history2 |
| Water | | WC Method | >0.05 | NEG | NEG | NEG |
| WEAR METAL | S | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >20 | 0 | 0 | 0 |
| Chromium | ppm | ASTM D5185m | >20 | <1 | 0 | 0 |
| Nickel | ppm | ASTM D5185m | >20 | 0 | 0 | 0 |
| Titanium | ppm | ASTM D5185m | | <1 | 0 | 0 |
| Silver | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >20 | 3 | 0 | 0 |
| Lead | ppm | ASTM D5185m | >20 | <1 | 0 | 0 |
| Copper | ppm | ASTM D5185m | >20 | <1 | 0 | 0 |
| Tin | ppm | ASTM D5185m | >20 | <1 | 0 | 0 |
| Vanadium | ppm | ASTM D5185m | | <1 | 0 | 0 |
| Cadmium | ppm | ASTM D5185m | | <1 | 0 | 0 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | 5 | 0 | 0 | 0 |
| Barium | ppm | ASTM D5185m | 5 | 0 | 0 | 0 |
| Molybdenum | ppm | ASTM D5185m | 5 | 0 | 0 | 0 |
| Manganese | ppm | ASTM D5185m | | 0 | <1 | 0 |
| Magnesium | ppm | ASTM D5185m | 25 | <1 | 0 | 0 |
| Calcium | ppm | ASTM D5185m | 200 | 4 | 0 | <1 |
| Phosphorus | ppm | ASTM D5185m | 300 | 354 | 286 | 310 |
| Zinc | ppm | ASTM D5185m | 370 | 5 | 0 | 0 |
| Sulfur | ppm | ASTM D5185m | 2500 | 409 | 194 | 398 |
| CONTAMINAN | TS | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >15 | 2 | 1 | 1 |
| Sodium | ppm | ASTM D5185m | | 0 | 3 | 0 |
| Potassium | ppm | ASTM D5185m | >20 | 1 | 1 | 0 |
| FLUID CLEANL | INESS | | limit/base | current | history1 | history2 |
| Particles >4µm | | ASTM D7647 | >10000 | 9501 | 3170 | 2682 |
| Particles >6µm | | ASTM D7647 | >2500 | 1243 | 214 | 450 |
| Particles >14µm | | ASTM D7647 | >640 | 64 | 20 | 54 |
| Particles >21µm | | ASTM D7647 | >160 | 20 | 4 | 13 |
| Particles >38µm | | ASTM D7647 | >40 | 2 | 0 | 1 |
| Particles >71µm | | ASTM D7647 | >10 | 0 | 0 | 0 |
| Oil Cleanliness | | ISO 4406 (c) | >20/18/16 | 20/17/13 | 19/15/11 | 19/16/13 |
| FLUID DEGRA | DATION | method | limit/base | current | history1 | history2 |
| Acid Number (AN) | mg KOH/g | ASTM D8045 | 0.57 | 0.27 | 0.25 | 0.25 |




OIL ANALYSIS REPORT











| VISUAL | | method | | | | history2 |
|-------------------------|--------|---------|-------|-------|-------|----------|
| White Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | NONE | NONE | NONE |
| Silt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Debris | scalar | *Visual | NONE | NONE | NONE | LIGHT |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.05 | NEG | NEG | NEG |
| Free Water | scalar | *Visual | | NEG | NEG | NEG |


| FLUID PROP | ERHES | method | | | history1 | history2 |
|-------------|-------|-----------|----|------|----------|----------|
| Visc @ 40°C | cSt | ASTM D445 | 68 | 68.3 | 67.0 | 66.5 |

| SAMPLE IMAGES | method | | history2 |
|---------------|--------|--|----------|
| | | | |

Color











Certificate L2367

Laboratory Sample No.

Lab Number : 06133230 Unique Number: 10952695 Test Package : IND 2

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : PCA0115888

Tested Diagnosed

Received : 29 Mar 2024 : 01 Apr 2024 : 03 Apr 2024 - Jonathan Hester

KraftHeinz - Kirksville - Plant 8333 PCA

2504 INDUSTRIAL DR KIRKSVILLE, MO

US 63501 Contact: Wilberto Pacheco Garcia

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Wilberto.PachecoGarcia@kraftheinz.com T:

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (660)627-5887