

OIL ANALYSIS REPORT

Area **INJECT B ROOM [98794455]** KR-GR-003106 - DUMPER 3B - SOUTH (S/N INJECT B - 11513037)

Hydraulic System

AW HYDRAULIC OIL ISO 68 (--- GAL)

DIAGNOSIS

Recommendation

We recommend you service the filters on this component if applicable. Resample at the next service interval to monitor. (Customer Sample Comment: 98794455)

Wear

All component wear rates are normal.

Contamination

There is a high amount of silt (particulates < 14 microns in size) present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0120396	PCA0088774	PCA0111166
Sample Date		Client Info		14 Mar 2024	22 Jan 2024	20 Dec 2023
	nrs	Client Info		0	0	0
-	nrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	Not Changd
Sample Status				ABNORMAL	ABNORMAL	ABNORMAL
CONTAMINATIC		method	limit/base			
	ЛN			current	history1 NEG	history2 NEG
Water		WC Method		NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron p	opm	ASTM D5185m	>20	0	0	0
Chromium p	opm	ASTM D5185m	>20	<1	0	0
Nickel p	opm	ASTM D5185m	>20	0	0	0
Titanium p	opm	ASTM D5185m		<1	0	0
Silver p	opm	ASTM D5185m		0	0	0
Aluminum p	opm	ASTM D5185m	>20	3	<1	0
Lead p	opm	ASTM D5185m	>20	<1	0	0
Copper p	opm	ASTM D5185m	>20	1	<1	<1
	pm	ASTM D5185m	>20	<1	0	0
1	opm	ASTM D5185m		<1	0	0
	opm	ASTM D5185m		<1	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron p	opm	ASTM D5185m	5	0	0	0
Barium p	opm	ASTM D5185m	5	0	0	0
	opm	ASTM D5185m	5	0	0	0
	opm	ASTM D5185m		0	<1	<1
	opm	ASTM D5185m	25	<1	0	0
	opm	ASTM D5185m	200	12	2	0
	opm	ASTM D5185m	300	465	420	398
	opm	ASTM D5185m		60	53	25
	opm	ASTM D5185m		888	727	589
CONTAMINANT	S	method	limit/base	current	history1	history2
	opm	ASTM D5185m		3	2	2
	opm	ASTM D5185m		<1	2	4
	opm	ASTM D5185m	>20	1	0	1
FLUID CLEANLI	VESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>10000	59992		▲ 36760
Particles >6µm		ASTM D7647		▲ 7749		2805
Particles >14µm		ASTM D7647	>640	338		110
Particles >21µm		ASTM D7647 ASTM D7647		60		22
		ASTM D7647 ASTM D7647	>100	3		1
Particles >38µm Particles >71µm		ASTM D7647 ASTM D7647		0		0
Oil Cleanliness		ISO 4406 (c)	>10 >20/18/16	u <u> 4</u> 23/20/16		0
FLUID DEGRADA		()	limit/base	current	history1	history2
		ASTM D8045	0.57	0.22		0.22
Acid Nulliber (AIN)	ng KOH/g	A311VI D6045	0.57	0.22		0.22


Report Id: KRAKIR [WUSCAR] 06133255 (Generated: 04/03/2024 15:29:06) Rev: 1


Submitted By: Wilberto Pacheco Garcia


Page 1 of 2




OIL ANALYSIS REPORT










VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	0.2%	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	68	67.2	67.0	66.4
SAMPLE IMAG	GES	method	limit/base	current	history1	history2
Color						
Bottom				631		(6)



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

Submitted By: Wilberto Pacheco Garcia

F: (660)627-5887