

OIL ANALYSIS REPORT

Sample Rating Trend







0008 Component Diesel Engine Fluid AW HYDRAULIC OIL ISO 32 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

Machine Id

All component wear rates are normal.

Contamination

There is no indication of any contamination in the fluid.


Fluid Condition

The condition of the fluid is acceptable for the time in service.

SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0117706		
Sample Date		Client Info		20 Mar 2024		
Machine Age	mls	Client Info		0		
Oil Age	mls	Client Info		0		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0		
Water		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	3		
Chromium	ppm	ASTM D5185m	>20	<1		
Nickel	ppm	ASTM D5185m	>4	0		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m	>3	0		
Aluminum	ppm	ASTM D5185m	>20	2		
Lead	ppm	ASTM D5185m	>40	1		
Copper	ppm	ASTM D5185m	>330	20		
Tin	ppm	ASTM D5185m	>15	<1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	5	5		
Barium	ppm	ASTM D5185m	5	0		
Molybdenum	ppm	ASTM D5185m	5	<1		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m	25	2		
Calcium	ppm	ASTM D5185m	200	101		
Phosphorus	ppm	ASTM D5185m	300	559		
Zinc	ppm	ASTM D5185m	370	819		
Sulfur	ppm	ASTM D5185m	2500	1880		
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	6		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	<1		



OIL ANALYSIS REPORT



	VISUAL		method	limit/base	current	history1	history2
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
Mar20/24 -	Appearance	scalar	*Visual	NORML	NORML		
Mar2	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
	Free Water	scalar	*Visual		NEG		
	FLUID PROPE		method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	32	46.5		
	GRAPHS						
	Iron (ppm)				Lead (ppm)		
	250 Severe			100	Severe		
	200 1			80			
	Abnormal			Ed 60			
				40	Abnormal - G	*****	
	50 -			20			
	24 0			24			74
	Mar20/24			Mar20/24	Mar20/24		Mar20/04
	—			≥			2
	Aluminum (ppm)			50	Chromium (pp	om)	
	40 Severe			40	Severe		
	_ 30			_ 30			
	20 Abnormal			³⁰	Abnormal		
	10-			10	1.1		
	0						
	0/24 -						0/24 .
	Mar20/24			Mar20/24	Mar20/24		Mar20/24
	Copper (ppm)				Silicon (ppm)		
	400 Severe			80			
	300 -			60			
	E 200			틆 40			
	<u>E</u> 200 -			음.4U	Abnormal		1
	100			20			
	0			(
	Mar20/24			Mar20/24	Mar20/24		Mar20/24
				Ma	Ma		Mar
	Viscosity @ 100°C						
	Abnormal						
	Abnorma						
	(0 4						
	3						
	2						
	0/24			0/24			
	Mar20/24			Mar20/24			
Sample No. Lab Number	: WearCheck USA - 50 ⁻ : PCA0117706 : 06134313 : 10953778	1 Madiso Recei Teste Diagr	ved : 29 d : 02	, NC 27513 Mar 2024 Apr 2024 Apr 2024 - Se			H RIVERSID DESPLAINE RIVERSIDE, I US 6054

Contact/Location: Service Manager - VILNOR Page 2 of 2